ROOFTEC BREATHABLE MEMBRANE

120gsm

THE ROOFTEC BREATHABLE MEMBRANE IS AN AIRTIGHT, VAPOUR PERMEABLE MEMBRANE DESIGNED FOR USE IN BOTH FULLY SUPPORTED AND UNSUPPORTED INSTALLATIONS FOR TILED OR SLATE PITCH ROOFS. SUITABLE FOR BOTH WARM AND COLD ROOFING APPLICATIONS, AS WELL AS SCOTTISH SARKING BOARDS AND TIMBER AND METAL FRAMED CONSTRUCTION.

Benefits

- BBA certified
- · Conforms to BS5534.2014 Annex A
- Warm and cold applications
- UV stable for 3 months
- Vapour permeable
- Waterproof membrane
- Resistance to extreme temperatures
- Laboratory quality control

Suitability

- · The ceiling is well sealed
- Roof ridge height is not greater than 15 metres
- Roof pitch is between 12.5° and 75°
- Site altitude is not greater than 100m above sea level
- No significant site topography is present

Wind Zone Suitability


| | Batten Lap | | Tapered lap |
|--------|------------|-------|-------------|
| | 345mm | 250mm | 345mm |
| 120gsm | 1 - 3 | 1 - 5 | 1 - 5 |



| Product Code | Weight | Dimensions | Pallet Quantity |
|---------------------|--------|------------|-----------------|
| RPBM120150 | 120gsm | 1.0 x 50m | 35 |
| RPBM1201550 | 120gsm | 1.5 x 50m | 42 |



| SPECIFIC | CATIONS | |
|--|-------------------------|--|
| Reaction to fire | E-d2 Class | |
| Water vapour resistance | 0,02m (+0,020/-0,005) | |
| Flexibility at low temperature | -40°C | |
| Resistance to w | rater penetration | |
| Resistance to water penetration | W1 | |
| Tensile : | strength | |
| MD | CD | |
| efore artificial ageing: 245 N/50 mm (± 45) | 175 N/50 mm (± 45) | |
| After artificial ageing: 210 N/50 mm (± 45) | 150 N/50 mm (± 45) | |
| Elong | gation | |
| MD | CD | |
| Before artificial ageing: 50% (± 25) | 60% (± 25) | |
| After artificial ageing: 30% (± 20) | 40% (± 20) | |
| Resistance | to tearing | |
| MD | CD | |
| 130 N (± 30) | 140 N (± 30) | |
| Description | of product | |
| Weight | 120 g/m² | |
| Thickness | 0,55 mm | |
| Material | Polypropylene | |
| Composition | 3 | |
| Temperature resistance | from -40°C to +80°C | |
| Water vapou | r permeability | |
| 23°C/85%RH | 1400 g/m² x 24h (± 200) | |
| THE RESERVE OF THE PARTY OF THE | 3200 g/m² x 24h (± 400) | |
| 38°C/90%RH | | |
| 38°C/90%RH Dangerous substances | none | |



Storage

- Should be stored in dry, covered areas
- Sheltered from the sun
- Should be stored away from heat sources and fire.

Application Information



Membrane is placed directly over the rafters on the insulating material. Stretch horizontally over the entire roof surface.




EN 13859-2:2010 Flexible sheets for waterproofing. Part 2: Underlays for walls.

The overlap at the ridge should be at least 20cm.



Overlap the membrane sheeting by 15cm (red guide line). Overlap by at least 20cm with a pitch of under 22°.



Seams, overlaps, butt joints and damage to membrane can be masked with membrane adhesive tape. Connections to other substrates, e.g. masonry, should be made with silicon or self adhesive butyl tapes.







