

Installation guidance

Thistle® BoardFinish

TIMES ARE APPROXIMATE

0 mins



Add approx 11.5 litres of clean water per 25kg bag to mixing bucket. Gradually add the plaster to water whilst mixing



Complete 1st coat (1mm thick)

20 - 40 mins



Complete 2nd coat, the total thickness for both coats should be a minimum of 2mm

40 - 55 mins



Closing in

90 mins



1st trowel

100 mins


2nd trowel

120 mins

Final trowel to a matt finish (lubricated with minimal water)

Note:

Ensure that the product is suitable for the background to which it is being applied by using the Thistle Plaster Selector Guide.



Finishing times are **reduced** by suction



Finishing times are **extended** by cold weather conditions

Times and processes are given as guidance. On site practice may vary.