



# C5000- Exterior Latex Siding Stain

## Technical Specifications

### PRODUCT DESCRIPTION

C5000 Exterior Latex Flat is a 100% Acrylic formulation designed to be applied to most exterior surfaces. C5000 is specifically formulated to provide outstanding covering power, tenacious adhesion, excellent weathering capabilities and color retention. C5000 is an excellent choice to protect vertical wood siding while showing the texture of the wood..

### SPECIFICATIONS

<b>Type:</b>	100% Acrylic Resin	<b>Dry Time - Touch:</b>	30 Minutes
<b>Sizes:</b>	1's and Quarts	<b>Dry Time - Recoat:</b>	2 to 4 Hours
<b>Bases:</b>	One Coat White, White, Pastel, Midtone, Accent	<b>Full Service:</b>	14 Days
<b>Gloss:</b>	2-6% @ 85 <sup>0</sup>	<b>Flash Point:</b>	None
		<b>VOC:</b>	less than 50 g/L
		<b>% Solids Volume:</b>	35.4
		<b>Weight Per Gallon:</b>	11.57 +/- .20

### PRODUCT USE

#### Surface preparation

Clean surface to remove contaminants such as dirt, dust, oil, grease, wax and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. Patch holes and cracks, sand smooth and remove sanding dust.

**New Wood:** Make certain any "mill glaze" is removed prior to staining. Opaque stains are designed for application as one or two finish coats directly to bare wood. A primer should only be used if the surface is a severely staining wood such as T1-11 plywood siding, redwood or cedar. In severe cases, a stain blocking oil-based primer is recommended. See your C2 dealer for details.

**Painted Surfaces:** Remove all loose or peeling paint. Dull glossy surfaces. Prime surface as required using C3000 Exterior Latex Primer. Finish with one or two coats of C5000 Exterior Latex Siding Stain.

**Masonry Surfaces:** New masonry must be fully cured (90 days). For existing masonry, use pressure washer to remove chalked and peeling paint. Finish with one or two coats of C5000 Exterior Latex Siding Stain.

#### Application

C5000 Exterior Latex Siding Stain may be applied by roller (no less than 3/8 inch nap), brush (synthetic), pad or spray.

**Spreading Rate:** Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters) The spreading rate is determined by application to the smooth side of the siding. Spreading rate will be less if applied to the rough side of the siding.

**Thinning:** Do not thin.

**Airless Spray:** Use a 12 to 15 mil size tip.

**Cleanup:** Clean painting equipment and spills immediately using warm soapy water.

**Limitations: Do not apply if product, air or surface temperature is below 50<sup>0</sup> F (10<sup>0</sup> C) - Keep product from freezing.** Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.

**Disposal:** Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. See your C<sup>2</sup> dealer for disposal recommendations in your area.



# C5100- Exterior Latex Matte

## Technical Specifications

### PRODUCT DESCRIPTION

C5100 Exterior Latex Matte is a 100% Acrylic formulation designed to be applied to most exterior surfaces. C5100 is specifically formulated to provide outstanding covering power, tenacious adhesion, excellent weathering capabilities and color retention. C5100 is an excellent choice to renew siding.

### SPECIFICATIONS

<b>Type:</b>	100% Acrylic Resin	<b>Dry Time - Touch:</b>	30 Minutes
<b>Sizes:</b>	1's and Quarts	<b>Dry Time - Recoat:</b>	2 to 4 Hours
<b>Bases:</b>	White, Pastel, Midtone, Accent	<b>Full Service:</b>	14 Days
<b>Gloss:</b>	3-7% @ 85 <sup>0</sup>	<b>Flash Point:</b>	None
		<b>VOC:</b>	less than 50 g/L
		<b>% Solids Volume:</b>	40.9
		<b>Weight Per Gallon:</b>	11.58 +/- .25

### PRODUCT USE

**Surface preparation:** Clean surface to remove contaminants such as dirt, dust, oil, grease, wax and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. Patch holes and cracks, sand smooth and remove sanding dust.

**New Wood:** Spot prime all knots and sappy areas with A9100 Exterior Alkyd Primer. Allow primed areas to dry and sand until smooth. Apply one coat of C3000 Exterior Latex Primer to entire surface. If required, sand knots again and remove dust. Finish with one or two coats of C5100 Exterior Latex Matte. Note: For tannin containing woods, best results are achieved by priming with A9000 Exterior Alkyd Primer.

**Painted Surfaces:** Remove all loose or peeling paint. Dull glossy surfaces. Prime entire surface as required using C3000 Exterior Latex Primer. Finish with one or two coats of C5100 Exterior Latex Matte.

**Galvanized Metal:** Clean surface with a high solvency Thinner. Prime using C3000 Exterior Latex Primer. Finish with one or two coats of C5100 Exterior Latex Matte.

**Aluminum/Vinyl Siding:** Clean surface using a pressure washer. Finish with one or two coats of C5100 Exterior Latex Matte. Note: Never use dark colors on aluminum or vinyl siding.

**Masonry Surfaces:** New masonry must be fully cured (90 days). For existing masonry, use pressure washer to remove chalked and peeling paint. Finish with one or two coats of C5100 Exterior Latex Matte.

#### Application

C5100 Exterior Latex Matte may be applied by roller (no less than 3/8 inch nap), brush (synthetic), pad or spray.

**Spreading Rate:** Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters)

**Thinning:** Do not thin.

**Airless Spray:** Use a 12 to 15 mil size tip.

**Cleanup:** Clean painting equipment and spills immediately using warm soapy water.

**Limitations: Do not apply if product, air or surface temperature is below 50<sup>0</sup> F (10<sup>0</sup> C) - Keep product from freezing.** Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.

**Disposal:** Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. See your C<sup>2</sup> dealer for disposal recommendations in your area.



# C5200- Exterior Latex Eggshell

## Technical Specifications

### PRODUCT DESCRIPTION

C5200 Exterior Latex Eggshell is a 100% Acrylic formulation designed for application to most exterior surfaces where a slight angular sheen is desired. C5200 is specifically formulated to provide outstanding covering power, excellent flow and leveling, tenacious adhesion and weathering characteristics (gloss and color retention) that are second to none.

### SPECIFICATIONS

<b>Type:</b>	100% Acrylic Resin	<b>Dry Time - Touch:</b>	30 Minutes
<b>Sizes:</b>	1's and Quart	<b>Dry Time - Recoat:</b>	2 to 4 Hours
<b>Bases:</b>	One Coat White, White, Pastel, Midtone, Accent	<b>Full Service:</b>	14 Days
<b>Gloss:</b>	15-25% @ 85 <sup>0</sup>	<b>Flash Point:</b>	None
		<b>VOC:</b>	less than 50 g/L
		<b>% Solids Volume:</b>	38.4
		<b>Weight Per Gallon:</b>	10.98 +/- .2

### PRODUCT USE

Surface preparation	Application
<p>Clean surface to remove contaminants such as dirt, dust, oil, grease, wax and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. Patch holes and cracks, sand smooth and remove sanding dust.</p> <p><b>New Wood:</b> Spot prime all knots and sappy areas with A9000 Exterior Alkyd Primer. Allow primed areas to dry and sand until smooth. Apply one coat of C3000 Exterior Latex Primer to entire surface. If required, sand knots again and remove dust. Finish with one or two coats of C5200 Exterior Latex Eggshell. Note: For tannin containing woods, best results are achieved by priming with A9000 Exterior Alkyd Primer.</p> <p><b>Painted Surfaces:</b> Remove all loose or peeling paint. Dull glossy areas. Prime entire surface as required using C3000 Exterior Latex Primer. Finish with one or two coats of C5200 Exterior Latex Eggshell.</p> <p><b>Galvanized Metal:</b> Clean surface with Lacquer Thinner. Prime using C3000 Exterior Latex Primer. Finish with one or two coats of C5200 Exterior Latex Eggshell.</p> <p><b>Aluminum/Vinyl Siding:</b> Clean surface using a pressure washer. Finish with one or two coats of C5200 Exterior Latex Eggshell. Note: Never use dark colors on aluminum or vinyl siding.</p> <p><b>Masonry Surfaces:</b> New Masonry must be fully cured (90) days). For existing masonry use pressure washer to remove chalked and peeling paint. Finish with one or two coats of C5200 Exterior Latex Eggshell.</p>	<p>C5200 Exterior Latex Eggshell may be applied by roller (no less than 3/8 inch nap), brush (synthetic) or spray.</p> <p><b>Spreading Rate:</b> Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters)</p> <p><b>Thinning:</b> Do not thin.</p> <p><b>Airless Spray:</b> Use a 12 to 15 mil size tip.</p> <p><b>Cleanup:</b> Clean painting equipment and spills immediately using warm soapy water.</p> <p><b>Limitations: Do not apply if product, air or surface temperature is below 50<sup>0</sup> F (10<sup>0</sup> C) - Keep product from freezing.</b> Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.</p> <p><b>Disposal:</b> Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. See your C<sup>2</sup> dealer for recommendations in your area.</p>



# C5300 – C2 Exterior Direct to Substrate Latex Satin Technical Specifications

<b>PRODUCT DESCRIPTION</b>			
C5300 Exterior Direct to Substrate Latex Satin is a 100% Acrylic formulation designed to be applied to most exterior surfaces without a primer. The C5300 series is specifically formulated to provide outstanding covering power, tenacious adhesion, excellent stain resistance, superior weathering capabilities and great color retention. The C5300 series is a great choice for both aluminum and vinyl siding.			
<b>SPECIFICATIONS</b>			
<b>Type:</b>	100% Acrylic	<b>Dry Time - Touch:</b>	30 Minutes
<b>Sizes:</b>	¼, 1's	<b>Dry Time - Recoat:</b>	2 to 4 Hours
<b>Bases:</b>	White, Pastel, Midtone, Accent	<b>Full Service:</b>	14 Days
<b>Gloss:</b>	15-25% @ 60 degrees	<b>Flash Point:</b>	None
		<b>VOC:</b>	Less than 50 g/L
		<b>% Solids Volume:</b>	38.0%
		<b>Weight Per Gallon:</b>	11.30 +/- .2
<b>PRODUCT USE</b>			
<p style="text-align: center;"><b>Surface preparation</b></p> <p>Clean surface to remove contaminants such as dirt, dust, oil, grease, wax and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. <b>(Wear protective eyewear, clothing and rubber gloves when treating mildew)</b> Patch holes and cracks, sand and remove sanding dust.</p> <p><b>New Wood:</b> Spot prime all knots and sappy areas with A9100 Exterior Alkyd Primer. Allow primed areas to dry and sand until smooth. If required, prime and sand knots again and remove dust. Finish with two coats of C5300 tinted to your desired color. <b>Note:</b> For tannin containing woods such as Redwood and Cedar apply one coat of C5300 and <b>let dry overnight</b>. Apply a second coat the next day. Try a test area first as severely staining wood may require A9100 Exterior Alkyd Primer to block the stain.</p> <p><b>Previously Painted Surfaces:</b> Remove all loose or peeling paint. Dull glossy surfaces by scuff sanding. "Prime" any bare spots with C5300 and then finish with one or two coats of C5300 tinted to your desired color.</p> <p><b>Galvanized Metal:</b> Clean surface with a high solvency thinner. Wipe clean and dry then finish with one or two coats of C5300.</p> <p><b>Aluminum/Vinyl Siding:</b> Make certain that all chalk is removed from surface by cleaning with a pressure washer or mechanical device if required. Finish with one but preferably two coats of C5300. <b>Note: Do not use dark colors on siding.</b></p> <p><b>Masonry Surfaces:</b> New masonry must be fully cured (90 days). Clean the surfaces with a pressure washer and apply two coats of C5300. For previously painted masonry, pressure wash and apply one or two coats.</p>		<p style="text-align: center;"><b>Application</b></p> <p>Stir thoroughly prior to applying with roller (no less than 3/8<sup>th</sup> inch), brush (synthetic), pad or spray.</p> <p><b>Spreading Rate:</b> Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters)</p> <p><b>Thinning:</b> Do not thin.</p> <p><b>Airless Spray:</b> Use a 12 to 15 mil size tip.</p> <p><b>Cleanup:</b> Clean painting equipment and spills immediately using warm soapy water.</p> <p><b>Limitations:</b> Do not apply if product, air or surface temperature is below 50<sup>o</sup>F (10<sup>o</sup> C)</p> <p><b>Keep product from freezing.</b></p> <p><b>Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.</b></p> <p><b>Disposal:</b> Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. See your C2 dealer for disposal recommendations in your area.</p>	



# C5400- Exterior Latex Semi-Gloss

## Technical Specifications

<b>PRODUCT DESCRIPTION</b>			
C5400 Exterior Latex Semi-Gloss is a 100% Acrylic formulation designed for application to most exterior surfaces where a semi-gloss finish is desired. C5400 is specifically formulated to provide outstanding covering power, exceptional flow and leveling, tenacious adhesion and weathering characteristics (gloss and color retention) that are second to none.			
<b>SPECIFICATIONS</b>			
<b>Type:</b>	100% Acrylic Resin	<b>Dry Time - Touch:</b>	30 Minutes
<b>Sizes:</b>	1's and Quarts	<b>Dry Time - Recoat:</b>	2 to 4 Hours
<b>Bases:</b>	One Coat White, White, Pastel, Midtone, Accent	<b>Full Service:</b>	14 Days
<b>Gloss:</b>	40 - 50% @60 <sup>0</sup>	<b>Flash Point:</b>	None
		<b>VOC:</b>	less than 50 g/L
		<b>% Solids Volume:</b>	37.6
		<b>Weight Per Gallon:</b>	10.86 +/- .2
<b>PRODUCT USE</b>			
<p style="text-align: center;"><b>Surface preparation</b></p> <p>Clean surface to remove contaminants such as dirt, dust, oil, grease, wax and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. Patch holes and cracks, sand smooth and remove sanding dust.</p> <p><b>New Wood:</b> Spot prime all knots and sappy areas with A9000 Exterior Alkyd Primer. Allow primed areas to dry and sand until smooth. Apply one coat of C3000 Exterior Latex Primer to entire surface. If required, sand knots again and remove dust. Finish with one or two coats of C5400 Exterior Latex Semi-Gloss. Note: For tannin containing woods, best results are achieved by priming with A9000 Exterior Alkyd Primer.</p> <p><b>Painted Surfaces:</b> Remove loose or peeling paint. Dull glossy surfaces. Prime entire surface as required using C3000 Exterior Latex Primer. Finish with one or two coats of C5400 Exterior Latex Semi-Gloss.</p> <p><b>Galvanized Metal:</b> Clean surface with Lacquer Thinner. Prime with one or two coats of C3000 Exterior Latex Primer. Finish with one or two coats of C5400 Exterior Latex Semi-Gloss.</p> <p><b>Aluminum/Vinyl Siding:</b> Clean surface using a pressure washer. Finish with one or two coats of C5400 Exterior Latex Semi-Gloss. Note: Never use dark colors on aluminum or vinyl siding.</p> <p><b>Masonry Surfaces:</b> New masonry must be fully cured (90 days). For existing masonry use pressure washer to remove chalked and peeling [paint. Finish with one or two coats of C5400 Exterior Latex Semi-Gloss.</p>		<p style="text-align: center;"><b>Application</b></p> <p>C5400 Exterior Latex Semi-Gloss may be applied by roller (no less than 3/8 inch nap), brush (synthetic) or spray.</p> <p><b>Spreading Rate:</b> Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters)</p> <p><b>Thinning:</b> Do not thin.</p> <p><b>Airless Spray:</b> Use a 12 to 15 mil size tip.</p> <p><b>Cleanup:</b> Clean painting equipment and spills immediately using warm soapy water.</p> <p><b>Limitations:</b> Do not apply if product, air or surface temperature is below 50<sup>0</sup> F (10<sup>0</sup> C) - Keep product from freezing. Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.</p> <p><b>Disposal:</b> Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. See your C<sup>2</sup> dealer for recommendations in your area.</p>	