

SabreSeal™ SG

SabreSeal SG is a mildew resistant (anti-fungal), neutral cure silicone sealant formulated specifically for sanitary-grade applications where high humidity and temperature exist. It will bond to form a durable, flexible, waterproof seal on most common wet area building materials.

Benefits

- Anti-fungal (Tested to ASTM G21)
- Complies with BS 5889 Type B
- Excellent adhesion - adheres to most common surfaces including glass, metals, plastics and wood
- Low dirt pick up
- Permanent flexibility
- Excellent external weathering properties and UV stability.
- Suitable for indoor and outdoor use
- Great tooling properties

Areas of Use

- Bathroom, toilet, and kitchen environments
- Suitable for sinks, baths, showers, washbasins, bedding tile accessories, and kitchen/bathroom fixtures.



- Suitable on glass, ceramics, tiles, enamel, aluminum, concrete, and stainless steel, and most grouts.

Limitations

- Do not use in conjunction with bitumen asphalt, or substrates that bleed oil, solvents or plasticisers.
- Do not use in the manufacture of aquariums or chlorinated water storage.
- Non overpaintable.
- Not suitable for bedding I. G Units.

Surface Preparation

The surfaces to be must be clean, dry and free from dust, grease and other contaminants. As quality of plastics can vary, always carry out adhesion tests prior to large scale use. Improve adhesion by wiping surface with white spirits (painted surfaces). Priming is generally not required, although we always advise testing small areas prior to use. Joint design should be as follows:

Minimum width: 5mm. Movement capacity will be impaired if the depth of the joint is greater than the width. For maximum movement accommodation, it is recommended that:

- 1** The joint depth should be no less than 5mm.
- 2** Joint depth should be 5mm for joints up to 10mm wide.
- 3** Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints.

For deep joints, reduce depth by using SABRE® FIX LF FOAM or a suitable joint backer rod. All joints should be designed so that the seal is placed in a position which does not retain water or form a water trap. Triangular fillets should be no less than 12mm across the face and should be finished with a flat or convex face. Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut at an angle of 45° with an opening slightly

larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the trigger and keeping the gun at a constant angle to the surface being sealed. To ensure a proper bond, always smooth the sealant down with a spatula or piece of wood. An improved joint appearance can be achieved by placing masking tape to both sides of the joint, removing within 5 minutes of application.

Application

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut cleanly at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the gun trigger and keeping the gun at a constant angle to the surface being sealed.

Smooth down within 10 minutes of application using a wetted spatula, piece of wood or wetted finger. Any excess sealant can be removed with white spirit.

Packaging & Shelf Life



Available colours: Transparent • White
Packaging size: 310ml Cartridge 25/ctn,
600ml Foil Pack 12/ctn



The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

New Zealand

+64 6 366 0007
40-42 Cambridge St South
Levin 5510

Melbourne

+61 3 8657 5507
67 Gateway Blvd
Epping, VIC 3076

Sydney

+61 2 9098 8244
Level 6, 10 Herb Elliott Ave
Sydney Olympic Park, NSW 2127