

1 Freedom From Holes (ASTM D6319-19, 7.3 & ASTM D5151-19)

Results			Requirement			Pass/Fail
Glove Size (Sample Size)	Physical Performance	Numbers Of Failure	Physical Performance	AQL	n [Ac Re]	-
M (200)	Water Leakage	1	No Leakage	2.5	200 (10 11)	Pass

Remark: n Means Sample Size, Ac Means Acceptance Number, Re Means Rejection Number.

2 Physical Dimensions (ASTM D6319-19, 7.4 & ASTM D3767-03(2020))

Results		Requirement			Pass/Fail
Physical Performance	Numbers Of Failure	Physical Performance	AQL	n [Ac Re]	-
See Test Data	0	Size: M Width: (95±10) mm Length: Min. 230 mm Finger Thickness: Min. 0.05 mm Palm Thickness: Min. 0.05 mm	4.0	13 (1 2)	Pass

Test Data:

Size	Specimen	Width (mm)	Length (mm)	Finger Thickness (mm)	Palm Thickness (mm)
M	1	94	257	0.120	0.085
M	2	95	251	0.121	0.085
M	3	95	252	0.123	0.085
M	4	95	255	0.120	0.082
M	5	95	252	0.120	0.085
M	6	95	255	0.118	0.081
M	7	95	255	0.129	0.083
M	8	95	252	0.120	0.081
M	9	96	254	0.123	0.088
M	10	95	252	0.129	0.083
M	11	95	251	0.120	0.085
M	12	95	251	0.115	0.080
M	13	96	255	0.115	0.085

Remark: n Means Sample Size, Ac Means Acceptance Number, Re Means Rejection Number.

3 Powder Residue For Powder Free Gloves (ASTM D6319-19, 7.6 & ASTM D6124-06(2017))

Size	Result	Requirement	Pass/Fail
M	0.3 mg	Max. 2.0 mg	Pass





End Of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

