

APPLICATION GUIDE

EVEREST TRADE - PENETRATING POLYURETHANE (PU)
CONCRETE DUSTPROOFER / FLOOR PRIMER & SEALER

SURFACE PREPARATION

- Ensure the surface to be sealed is fully clean and dry before application.
- Ensure surface is completely dry and free from condensation and damp.
- Remove any loose or flaking paint.

Please view the MSDS for this product for suitable surface temperatures for application.

APPLICATION

- Before application, thoroughly stir the sealer with a metal mixing paddle drill attachment, This will ensure the solvent and binder within the product is mixed correctly and not settled at the bottom of the container.
- We recommend this product is applied with either a medium pile double-armed roller kit with extension pole, this makes application easier and prevents bending of the roller arm. Or a sprayer can be used which makes application onto large areas much quicker.
 A paintbrush can be used on edges and hard to reach areas.

- Apply one coat of Everest Trade Paints Floor Primer and Sealer Paint using a floor roller. Allow at between 6 - 8 hours for the Everest Trade Paints Floor Primer and Sealer Paint to fully absorb into the concrete and dry. Ensure the surface is no longer tacky to the touch before applying the 2nd coat.
- We recommend applying 2 coats if the product is being used only as a concrete sealer for concrete floors, this will ensure the best result and performance.
- If this is being used as a floor primer before painting, only 1 coat is necessary.
- Apply two coats of topcoat using a roller. Apply in thin, even coats for the best results, this will minimise drying times and result in a more durable coating.
- Make sure the paint completely touches dry before applying the following coat and leave a minimum of 24 hours after finishing the final coat, before any vehicles or heavy machinery is allowed onto the floor.

STORAGE PRECAUTIONS

Store away from heat and naked flames. Secure lid between uses to prevent paint hardening. Store away from frost.

For further assistance please contact our technical department on 0800 043 8220