# TAMCO PAINT

### AUTOMOTIVE

## Extra Slow Glamour Clearcoat *HC4105*

**HC4105** Glamour Clear is the slower version of HC4100, which is a medium to high solids clearcoat that has excellent flow, leveling and gloss retention. At 45% solids it still provides plenty of film build for the custom and collision industry. As with many of the other Tamco® clears **HC4105** is manufactured from direct to metal resins. This means clear can be applied directly over properly sanded and cleaned metal where protection from the elements is required. Outstanding gloss and durability at a reasonable price. **HC4105** is to be used in temperatures over 90°F or when baking.



#### **Features & Benefits**

- Designed for extreme hot and humid conditions 90°F+
- Baking clear
- Multi use
- Ideal for Collision and Custom
- Overall/Spot
- High buff ability
- 45% solids content
- · Easy to spray / User friendly
- Direct to metal and aluminum
- 97-99% on gloss meter
- Very high UV resistance
- Durable (excellent weathering)
- Water white clarity

#### **Compatible Surfaces**

- Sanded metal or aluminum
- All Tamco® Basecoats, HC895 & CC3000
- Other premium basecoats, but no warranty implied

#### **Required products**

- Tamco® HH76XX series hardeners.
  - HH7605
  - HH7607

#### Optional

- HR1370
- HR1380
- HR1390
- Pot Life Extender
- HP1010 Fisheye Eliminator
- HR900 Retarder
- HP Flat
  - Flo N Go
- (See our" What Temperature should I choose PDF" for a guideline on which suits your current job)



#### **Extra Slow Glamour Clearcoat** HC4105

Surface Preparation:

Throughly clean with HR397 Wax and Grease Remover and wipe dry with clean cloth. Plastics: Clean with HR397 Wax and Grease Remover using a Scotch-Brite pad, wipe dry with clean cloth.

Mix Ratio:

	Component		Volume
, 	HC4105 Clear	Clear	4
	HH7605/7607	Activator	1

Note: <u>Use only Tamco® Reducers.</u> Our reducers are completely moisture free. Moisture in reducer will kill the shine of our clears.

#### Additives:



HR900 Retarder, Pot-Life Extender, HP1001 Accelerator, HH1010 Fisheye Eliminator: 1-2 oz per spray able Quart. HR Reducers: up to 10% HP Flat: Refer to our HP Flat TDS sheet for mixing instructions.

Air Pressure &

Gun Setups:



Gun Setups:

**HVLP** 

Siphon Feed: 1.2 mm – 1.4 mm Gravity Feed: 1.2 mm - 1.4 mm

#### Conventional

Siphon Feed: 1.2 mm – 1.4 mm Gravity Feed: 1.2 mm - 1.4 mm

25-29 PSI at the gun 5-10 PSI at the cap

Air Pressures Conventional: Always refer to your gun manual for their advice in using our products.





#### Application:



1. Allow Tamco basecoat to dry from 30 minutes to 8 hours.

2. Apply first medium-wet coat.

- 3. Allow 30-45 minute flash at 78°F between coats
- 4. Apply second wet coat. (Two coats are generally sufficient, unless you plan to cut and buff.)
- 5. Apply a 3rd coat and let sit overnight.
- 6. Flow Coat: Add 5-10% HR1390 Very Slow Reducer and apply 1 wet coat, followed by second wet coat with 45-60 minute flash times between coats.
- 7. Apply over Tamco® Base, HC895 Intercoat & Clearcoat or CC3000 Candy Carrier.

#### On Metal:

- Clean substrate first with soap and water.
  - Use Tamco® HR397 (or HR397W) Wax and Grease remover.
  - Dry sand substrate using 180 Grit to remove rust, or surface damage.
  - Dry sand substarte with 320 grit to remove your 180 grit scratches.
  - Finish with 400-600 grit.
- Clean the substrate again with HR397 (or HR397W) Wax and Grease remover.
  - Final Clean: Clean the substrate for the last time with HR398 Final Wipe.

#### Drying Times:



24-48 hours @ 78°F. Airdry:

Tape Time: 16 hours

Baking: 140°F for 30 minutes.

#### Wet Sanding:



Sand with 400-600 grit if re-coat is needed.

**Polishing:** 



Finish sanding. After 12-16 hour cure time, dry or wet sand adding a small amount of dish soap to water and wet sand with 800 grit and work your way to 1500-2000 grit then 3000 grit before buffing.

Follow the recommendations on the polish you use.

For best results use Tamco's® 2 step polish.

For show car gloss: Allow the vehicle to sit up to 3 or 4 days for a total gas-out of solvents before polishing. After finish sanding, when the clear is 'open' sit the vehicle in the sun for a full 24 hours.

#### Do not wax for 120 days





Tamco® Tips:



- 1. When air drying, a minimum temperature of 90°F should be maintained. Sanded surface should be re-sanded if not top- coated within 8 hours.
- 2. Extra reducer may be required In High Temps using HR1390 Very Slow Reducer or HR900 retarder.
- 3. When using hardeners, be sure the mixture is stirred throughly.
- 4. Apply over Tamco® Base, HC895 Intercoat & Clearcoat or CC3000 Candy Carrier.

Flow Coat: Add 5-10% HR1390 Very Slow Reducer and apply 1 wet coat, followed by second wet coat with 45-60 minute flash times between coats.

Note: Use only Tamco® Reducers.

**Equipment Cleaning:** 

Lacquer Thinner or HR1360 is an excellent cleaner.

**Cold Shop Conditions:** 

Do not spray HC4105 under 90°F.







### Extra Slow Glamour Clearcoat *HC4105*

#### **TECHNICAL DATA & PHYSICAL PROPERTIES**

Color: Clear Mix Ratio: 4:1 Viscosity: (RTS) 18-22 sec. EZ Zahn #2 Pot Life: 1-4 hours depending on temperature **Theoretical Dry Film:** 480 ft2 @ 1 Mil Weight Solids: 47% Color & Gloss Holdout: Excellent Volume Solids (RTS): 41% Humidity Resistance: Excellent Weight Per Gallon: 8.50 lbs. Solvent Resistance: Excellent Topcoat Times: 30 min. at 1 mils or less **Repair Ability: Excellent** Florida Exposure: Good Package VOC: 3.70 # / gal Chip Resistance: Good RTS VOC: 3.7 # / gal

#### See Safety Data Sheet/Material Safety Data Sheet and Labels for additional safety information and handling instructions.

Important: The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to direction, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Tamco Paint Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Tamco Paint warrant freedom from patent infringement in the use of any formula or process set forth herein.

Tamco Paint Barney Family Enterprises PO BOX 711 Wakefield, Va 23888 (757-627-9551)

www.TamcoPaint.com

Follow us online: @TamcoPaint



For more TDS Sheets, scan QR code



To contact us, scan QR code





(757) 627-9551