# Garment Printer &

## Glitter Flex ULTRA

Garmentprinterink.com 400 Oser Ave STE 2000 Hauppauge, NY 11788 631-858-0114



#### **Acceptable Fabrics**

Cotton, Uncoated Polyester, Cotton/Polyester Blends, Fabric Blends, Wool, Linen Excluding Nylon

#### Sizing Available

Available Widths (in.): 20" Available Lengths (yards) 1, 5, 10,15,20,30

#### **Special Precautions**

Sky Blue

GF-Ultra 32

Steel Blue

GF-Ultra 79

\*Starred colors are slightly translucent and will take on the color of the garment, especially black or dark garments.

COLOR VARIATION: During the manufacturing process, sometimes there is a slight color variation between rolls.



New Color!

GFU-Neon 122

### Thickness

13-15 mils/325-375 microns



60° Blade Recommended



Cut this material in mirror image



320°F - 330°F



Medium to Firm, even pressure



12 to 15 Seconds



Peel warm, use Teflon Sheet and re-press for 2 seconds



Wash warm, tumble dry normal. Suitable for dry-cleaning.



To sublimate: Heat sublimation on top of already pressed vinyl at 390°F for 30 seconds \*Paper heat settings may differ

Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics.