



Garmentprinterink.com
400 Oser Ave STE 2000
Hauppauge, NY 11788
631-858-0114



LOVE

what you PRESS!



REFLECTION PROTECTION™

REFLECTIVE HEAT TRANSFER FILM

PLEASE NOTE: NEW APPLICATION INSTRUCTIONS



Safety Silver RF-9501

Applications

Nylon and other heat sensitive fabrics.



60° Blade
Slow cutting
speed



Remove heat liner.
Cut this material
in mirror image



320°F



Firm
even
pressure



3 - 5 seconds



Peel cold, then cover
with Teflon & repress
for 10-15 seconds, let
cool then remove Teflon



Wash inside out.
Warm water, gentle cycle.
Tumble dry low heat.
Suitable for dry-cleaning.

Test on dazzle cloth, shiny polyester or moisture-wicking materials.



Safety Silver RF-9505

Applications

Cotton and Cotton-Blend Fabrics



60° Blade
Slow cutting
speed



Remove heat liner.
Cut this material
in mirror image



275°F - 305°F



Firm
even
pressure



3 - 5 seconds



Peel cold, then cover
with Teflon & repress
for 10-15 at 300°F - 305°F
seconds, let cool, remove Teflon



Wash inside out.
Warm water, gentle cycle.
Tumble dry low heat.

No nylon. Test on dazzle cloth, shiny polyester, and moisture-wicking materials.

GarmentPrinterInk.com 400 Oser Ave STE 2000 Hauppauge, NY 11788 631-858-0114

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.