

# Siser HTV APPLICATION INSTRUCTIONS

## EasyWeed<sup>®</sup>, EasyWeed<sup>®</sup> Electric, EasyWeed<sup>®</sup> Glow in the Dark

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (EasyPress<sup>®</sup> users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyWeed<sup>®</sup> EcoStretch<sup>™</sup>

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Lycra<sup>®</sup>/Spandex



### Application Instructions (Home Iron):

- Set iron dial on Cotton.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium pressure for 10-15 seconds.
- Peel carrier hot.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 250°F / 120°C (EasyPress users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## EasyWeed<sup>®</sup> Extra

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Nylon



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (EasyPress users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

## EasyWeed<sup>®</sup> Stretch

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Nylon



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with firm pressure for 20 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C (EasyPress users add approx. 30°).
- Use firm pressure for 20 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

### RECOMMENDED ACCESSORIES:

Siser<sup>®</sup> EasyWeeder<sup>®</sup>, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



**GARMENT  
PRINTER INK**

(631) 858-0114

[sales@garmentprinterink.com](mailto:sales@garmentprinterink.com)

# Siser HTV APPLICATION INSTRUCTIONS

## EasyWeed® Sub Block

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended.)
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 265°F / 130°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Hang item to dry.

## EasyWeed® Adhesive

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended.)
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 275°F / 135°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot then apply top layer.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyPatterns® Plus

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended.)
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyReflective®

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather | Lycra®/Spandex



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended.)
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm (wait at least 15 seconds off press).

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



**GARMENT  
PRINTER INK**

**(631) 858-0114**

**sales@garmentprinterink.com**

# Siser HTV APPLICATION INSTRUCTIONS

## Easy® Glow

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium pressure 15 seconds.
- Peel carrier warm or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm or cold (5-10 seconds off press).

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## Easy® Puff

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester  
*Easy Puff is not recommended for use with a home iron.*



### IMPORTANT APPLICATION NOTES:

*Easy Puff* is designed to withstand only one heat application. Repeated applications will “flatten” the puff effect permanently. It is recommended to apply *Easy Puff* last when used with other materials. It is not recommended for use with a home iron.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 280°F / 138°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 8-10 seconds.
- Peel carrier hot.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

## Aurora™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier completely cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier completely cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## BlackBoard®

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material.
- Preheat garment for 2-3 seconds.
- Apply design at 275°F / 135°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



**GARMENT  
PRINTER INK**

**(631) 858-0114**

**sales@garmentprinterink.com**

# Siser HTV APPLICATION INSTRUCTIONS

## Brick® 600

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 20 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 310°F / 155°C. (*EasyPress* users add approx. 30°).
- Use medium pressure for 20 seconds.
- Peel carrier cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Glitter

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C. (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier warm.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Holographic

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather

*Holographic Rainbow Pearl gives your designs an opalescent finish that changes depending on the color of the garment. The material will not look the same on a black garment as it will on a white garment.*



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C. (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15-20 seconds.
- Peel carrier cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Metal

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C. (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



**GARMENT  
PRINTER INK**

**(631) 858-0114**

**sales@garmentprinterink.com**

# Siser HTV APPLICATION INSTRUCTIONS

## Sparkle™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15-20 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## StripFlock® Pro

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 311°F / 155°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier warm.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Twinkle™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15 seconds.
- Peel carrier warm.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



**GARMENT  
PRINTER INK**

**(631) 858-0114**

**sales@garmentprinterink.com**