

TECHNICAL DATA SHEET

PUR IT-2440

Туре	Standard polyester foam.
Colour	Light gray
Foam density	$24 + - 2 \text{ kg/m}^3$
DIN EN ISO 845	
CLD at 40% deformation	4.0 kPa+/-15%
DIN EN ISO 3386/1	
Compression set at 50% deformation	max. 10 %
DIN EN ISO 1856	
Elongation at break	min. 150 %
DIN EN ISO 1798	
Tensile strength	min. 100 kPa
DIN EN ISO 1798	
Numbers of cells	18-24 cells/cm
ISO 6915	

Thickness tolerances:

1.8 mm - 8.0 mm = +/- 0.2 mm 8.1 mm - 15 mm = +/- 0.3 mm 15.1 mm - 20 mm = +/- 0.4 mm

Application conditions:

Surface must be free from oil, fat, dust, humidity, grease, solvents or any other separators. Apply at room temperature.

The above given information should be considered as a guide but cannot be considered as binding and company accepts no liability. It is the customer responsibility to check if the material is suitable for its application. Please see "Guide to storing and application".

Version: 06.03.2014, 1,1

Matična št.: 5540917, ID št. za DDV: SI51492342 Št. reg. Vložka 1/14229/00 sodišče v Ljubljani Transakcijski račun: SI56 3000 0001 4723 569 Pladent d.o.o., PC Žeje pri Komendi Pod hrasti 18, 1218 Komenda Tel.+386 1 834 56 90/91