

Technical Specifications

Updated 6/6/22

CIS Core-Shell Quantum Dots In Water


Composition	Copper Indium Sulfide / Zinc Sulfide
Stabilizing ligand	Carboxylic Acid Group
Concentration	Order amount dependent
Organic Impurities	<1% (not including ligands)
Solvent*	DI Water
Volume	Order amount dependent
Lifetime	Six months if stored properly. Dark at 2-8°C
PL FWHM (nm)	<125
Quantum Yield	>15%
pH Stability	6-9
Buffer Stability	Borate, Tris, HEPES, PBS, MES, etc.

*Other solvents are available upon request.

Catalogue #	UV peak (nm)	Emission Peak (nm)	nmol/mg
CISW-530	NA	530±15	9.1
CISW-560	NA	560±15	7.1
CISW-590	NA	590±15	5.2
CISW-620	NA	620±15	3.5
CISW-650	NA	650±15	1.7
CISW-700	NA	700±15	1.2
CISW-750	NA	750±15	1.0

NNCrystal US Corporation

534 W Research Center Blvd., Ste 260, Fayetteville, AR 72701
Phone: 479.595.0662; Fax: 479.595.0570; E-mail: contact@nn-labs.com



NNCrystal US Corporation

Catalogue #	Core diameter (nm)	Shell Thickness (nm) **	Total Diameter (nm)
CIS-530	2.0±0.5	2.0	4.0±0.5
CIS-560	2.5±0.5	2.0	4.6±0.5
CIS-590	3.0±0.5	2.3	5.2±0.5
CIS-620	3.3±0.5	2.3	5.5±0.5
CIS-650	3.5±0.5	2.5	5.8±0.5
CIS-700	3.8±0.5	2.5	6.0±0.5
CIS-750	4.2±0.5	2.7	6.6±0.5

**Thickness of shell is expressed as total diameter added to core.