



# NNCrystal US Corporation

## Methylated Gold Nanoparticles

### Technical Data:

Core diameter: 5-100nm (Coefficient of Variance < 12%)

Polydispersity Index (PDI): <0.150

Amount: OD=50

Absorption Peak: 515-570nm (Size Dependant)

Number of Biotin Groups on Surface:  $\sim 4/\text{nm}^2$

Solvent: USP Grade Purified H<sub>2</sub>O

Storage: Store at 4°C. Do not freeze.

Lifetime: If stored properly the nanoparticles are stable for at least 12 months.

### Specifications for each size:

Diam. (nm)	Peak SPR (nm)	NPS/mL	Wt. Conc (mg/mL)	Molar Ext (M-1cm-1)	Size Dispersity (+/-nm)	Particle Volume (nm <sup>3</sup> )	Surface Area (nm <sup>2</sup> )	Surface / Volume Ratio	Particle Mass (g)	Molar Mass (g/mol)	Molar Conc.
5	515-520	5.47E+13	6.94E-02	1.10E+07	<15%	6.54E+01	7.85E+01	1.200	1.27E-18	7.64E+05	9.08E-08
10	515-520	5.98E+12	6.07E-02	1.01E+08	<15%	5.24E+02	3.14E+02	0.600	1.02E-17	6.11E+06	9.93E-09
15	520	1.64E+12	5.61E-02	3.67E+08	<12%	1.77E+03	7.07E+02	0.400	3.43E-17	2.06E+07	2.72E-09
20	524	6.54E+11	5.31E-02	9.21E+08	<12%	4.19E+03	1.26E+03	0.300	8.12E-17	4.89E+07	1.09E-09
30	526	1.79E+11	4.91E-02	3.36E+09	<12%	1.41E+04	2.83E+03	0.200	2.74E-16	1.65E+08	2.98E-10
40	530	7.15E+10	4.65E-02	8.42E+09	<12%	3.35E+04	5.03E+03	0.150	6.50E-16	3.91E+08	1.19E-10
50	535	3.51E+10	4.45E-02	1.72E+10	<10%	6.54E+04	7.85E+03	0.120	1.27E-15	7.64E+08	5.83E-11
60	540	1.96E+10	4.30E-02	3.07E+10	<10%	1.13E+05	1.13E+04	0.100	2.19E-15	1.32E+09	3.25E-11
70	548	1.20E+10	4.17E-02	5.03E+10	<10%	1.80E+05	1.54E+04	0.086	3.48E-15	2.10E+09	1.99E-11
80	553	7.82E+09	4.06E-02	7.70E+10	<10%	2.68E+05	2.01E+04	0.075	5.20E-15	3.13E+09	1.30E-11
90	564	5.37E+09	3.97E-02	1.12E+11	<8%	3.82E+05	2.54E+04	0.067	7.40E-15	4.46E+09	8.92E-12
100	572	3.84E+09	3.89E-02	1.57E+11	<8%	5.24E+05	3.14E+04	0.060	1.02E-14	6.11E+09	6.37E-12