# HYUNDAI SOLAR MODULE



**G12 PERC Shingled** HiE-S410DG(FB) HiE-S415DG(FB) HiE-S420DG(FB)





Shingled Technology

For Both Residential & Commercial **Applications** 



More Power Generation In Low Light



G12 PERC Shingled

G12 PERC Shingled Technology provides ultra-high efficiency with better performance in low irradiation. Maximizes installation capacity in limited space.



**Mechanical Strength** 

Tempered glass and reinforced frame design withstand rigorous weather conditions such as heavy snow and strong wind



**Reliable Warranty** 

Global brand with powerful financial strength provide reliable 25-year warranty. (Australia and Europe Only)



Hyundai's R&D center is an accredited test laboratory of both UL and VDE.

#### Hyundai's Warranty Provisions



YEARS

#### **25-Year Product Warranty** On material and workmanship

Australia and Europe Only 25

## • 25-Year Performance Warranty

 Initial year: 98.0% · Linear warranty after second year: with 0.55%p annual degradation, 84.80% is guaranteed up to 25 years

### About Hyundai Energy Solutions Co., Ltd

Established in 1972, Hyundai Heavy Industries Group is one of the most trusted names in the heavy industries sector and is a Fortune 500 company. As a global leader and innovator, Hyundai Heavy Industries is committed to building a future growth engine by developing and investing heavily in the field of renewable energy.

As a core energy business entity of HHI, Hyundai Energy Solutions has strong pride in providing High-quality PV products to more than 3,000 customers worldwide.

Certification





### **Flectrical Characteristics**

Electrical Characteristics		Mono-Crystalline Module (HiE-SDG(FB))		
		410	415	420
Nominal Output (Pmpp)	W	410	415	420
Open Circuit Voltage(Voc)	V	41.4	41.5	41.6
Short Circuit Voltage (Isc)	А	12.65	12.80	12.92
Voltage at Pmax (Vmpp)	V	34.4	34.4	34.5
Cuurent at Pmax (Impp)	А	11.97	12.08	12.19
Module Efficiency	%	20.6	20.9	21.1
Cell Type	-	PERC Mono-Crystalline Silicon Shingled		
Maximum System Voltage	V	1,500		
Temperature Coefficiency of Pmax	%/°C		-0.34	
Temperature Coefficiency of Voc	%/°C	-0.27		
Temperature Coefficiency of lsc	%/°C	0,04		

\*All data at STC(Standard Test Conditions). Above data may be changed without prior notice. \*Tolerance of Pmax:0~+5W.


\*Measuring uncertainty of power: ±3%.


\* Performance deviation of Voc [V], Isc [A], Vm[V] and Im[A]: $\pm$ 3%.

#### **Mechanical Characteristics**


Dimensions	1,812 $\times$ 1,096 $\times$ 30 mm (L $\times$ W $\times$ H)				
Weight	20.8kg				
Solar Cells	305 Cells, PERC Mono-crystaline Shingled (210 $ imes$ 210mm)				
Output Cables	4mm <sup>2</sup> ,+500mm/-1100mm(Vertical), +220mm/-180mm(Horizontal) Connector Stäubli : MC4-Evo2				
Junction Box	IP68, TUV&UL, two diodes				
Construction	Front Glass: AR Coated tempered glass, 3.2mm Encapsulation: EVA (Ethylene–Vingl-Acetate)				
Frame	Anodized Aluminum				

#### Module Diagram (Unit: mm)









# **Installation Safety Guide**

- Only qualified personnel should install or perform maintenance.
- Be aware of dangerous high DC voltage.
- Do not damage or scratch the rear surface of the module.
- Do not handle or install modules when they are wet.

Nominal Operating Cell Temperature	42.3℃(±2℃)	
Operating Temperature	-40 ~ 85 ℃	
Maximum System Voltage	DC 1,500 / 1,000 (IEC)	
Fire Rating	Class C	
Series Fuse Rating [A]	25	
Maximum Surface Load Capacity	Front 5,400 Pa Rear 2,400 Pa	

#### **I-V Curves**

