

A POURABLE, FAST & EFFECTIVE CONCRETE PATCH REPAIR SYSTEM.

FastPatch 3-2-1 is easily mixed and applied, simply add 3 parts powder to 1 part of water. Stronger than concrete, suitable for internal and external applications and ready for vehicular traffic in just 2 hours.

- ✓ Just add water (3 parts powder to 1 water), mix and pour
- ✓ Feather edge to 100mm+
- ✓ Good slip resistance
- ✓ Suitable for internal and external areas
- ✓ Can be applied to damp surfaces
- ✓ Fibre reinforced and stronger than concrete
- ✓ Solvent free low odour formula
- ✓ Can be applied between 5-30°C

Surface Preparation

Ensure surfaces are clean and free from any sitting water. Heavily trafficked areas should ideally have edges cut to 10mm+

Mixing

Remove the bag of powder from the container. The container makes an ideal mixing vessel. FastPatch is a simple 3 part powder to 1 part water mix. Always add the powder to the water to make mixing easier and achieve a pourable mix. Small amounts can be mixed by hand with a wide bladed tool. Large quantities are best mixed with an electric drill and mixing blade. Always ensure you incorporate all the product from around the edges of the mixing container. Use ASAP as the product will start to harden quickly. Remaining powder can be stored in a dry place and used later.

Application

Once a uniform consistency is achieved, pour the FastPatch 3-2-1 into the hole. It will flow freely but may require trowelling. Application depths are between 5mm – 100mm, although lightly trafficked areas can be feather edged. Pot life is 5-10 mins @ 20°C.

Curing Times @ 15-20°C:

Foot Traffic: 1 hour

Vehicle Traffic: 2 hours

Full chemical resistance is achieved over 7 days.

Pot Life

5 to 10 minutes at 20°C.

Coverage

10kg will cover approximately 0.2m² @ 25mm thick.

Shelf Life

One year in sealed containers.

Strength

Compressive strength at 20 °C:

Day 1: >20N/mm²

Day 7: >35N/mm²

Day 28: >45N/mm²

Cleaning Tools

Wash and scrub with clean water straight after use.

VIRTUS RESINS

The Shippon, Faenol

Pentrecelyn

Ruthin LL15 2SP

Tel: 01978 790 744

Tel: 0843 289 8422

Email: info@epoxyresinsuppliers.co.uk

www.epoxyresinsuppliers.co.uk