



1.1 oz Ripstop Nylon (calendered) Data Sheet

Width	~58 in (147 cm)
Weight	1.1 oz/yd ² (34 g/m ²)
Composition	100% Nylon
Yarn	Nylon
Denier	20D
Thread Count	Warp - 200, Weft - 180, Threads/inch
Thickness	0.0020 in (0.05 mm)
Grid Size/Shape	0.04 in x 0.04 in (1 x 1 mm) box
Finish/Coating	Calendered
DWR	Yes - Organic fluorine resin - 17.5-18.5%
Downproof	Yes
Care Instructions	Machine wash, delicate cycle. Wash Separately. Use a mild detergent, without fabric softener. Do not use bleach, conditioners or stain removers. Do Not Iron.
Country of Origin	Import
Digital Print	None

Property	Test Method	Value
Tear Strength	ASTM D 1424	Warp 2.2 lbF
		Weft 2.1 lbF
Tensile Strength	ASTM D 5034	Warp 24.7 lbF/in
		Weft 21.5 lbF/in
Air Permeability	ASTM D 737	0.302 ft ³ /ft ² /min (CFM)
Hydrostatic Head (pre-wash)	AATCC 127	N/A
Hydrostatic Head (post 10x wash)	AATCC 127 + AATCC 135	N/A
Seam Strength	ASTM D 1683	Warp 10.4 lbF
		Weft 13.8 lbF
Color Fastness to Light	AATCC 16	1.0
UV Transmission	AATCC 183	Mean UV Protection Factor (UPFm) - 13 UV -A Blocking(mean) - 83.85% UV -B Blocking(mean) - 94.54% UPF Class - < 15
Abrasion Resistance	ASTM D 4966	>10,000 Revolution

Possible Applications:

Great for projects such as top quilts, under quilts, sleeping bags, pillows, jackets, garment lining material, and lightweight stuff sacks/bags.

(1) Actual material properties will vary. Values listed represent average values or estimates.

(2) Disclaimer - All information, data, recommendations, etc provided for Ripstop by the Roll products (the Information) is produced for reference only. Ripstop by the Roll assumes no liability arising from (i) the application, processing, or use made of the Information or products; (ii) infringement of the intellectual or industrial property rights of third parties by reason of the application, processing, or use of the Information or products by the Buyer. Buyer shall (i) assume such liability; and (ii) verify the information and the products.



Ripstop by the Roll LLC