

REPORT NO.: T214-16-02718

PAGE : 2 OF 2

01. ADHESION STRENGTH (ASTM D2724-07 : 2015, C.R.E) : N/5 cm

#1		#2	#3	#4	
AS RECEIVED					
-WARP	14.2	12.7	12.4	12.9	
-WEFT	14.4	14.4	14.3	14.6	
AFTER 10TH WASHING					
-WARP	10.6		11.0	12.4	
-WEFT	12.3	14.1	13.2	13.9	

NOTE) CEMENT TYPE : LOCTITE 401 CYANOACRYLATE NON SOLVENT TYPE WASHING CONDITION : AATCC 135:2015, TEST NO. (2)(III)A(ii); MACHINE WASH DELICATE CYCLE AT (41 ± 3) $\mathrm{^{\circ}C}$, TUMBLE DRY DELICATE.

02. WATER VAPOUR PERMEABILITY (JIS L 1099 : 2012, B-1, POTASSIUM ACETATE METHOD) : g/m²/24 h

#1	#2	#3	#4
26 507	26 440	26 170	26 992

NOTE) CUP AREA: 0.002 374 6 m²

THE TEST RESULT WAS CONVERTED INTO 24 H UNITS.

03. WATER RESISTANCE (AATCC 127 : 2014, HYDROSTATIC PRESSURE TEST) : cmH₂O(mmH₂O)

#1	#2	#3	#4		
906(9 060)	918(9 180)	908(9 080)	956(9 560)		

NOTE) WATER PRESSURE: 60 cmH₂O/min(600 mmH₂O/min)

04. WATER REPELLENCY (AATCC 22: 2014, SPRAY TEST)

`		#1			#2			#3			#4	
AS RECEIVED	80	80	80	80	80	80	80	80	80	80	80	80
AFTER THE 3RD WASHING	80	80	80	80	80	80	80	80	80	80	80	80
AFTER THE 10TH WASHING	80	80	80	80	80	80	80	80	80	80	80	80

NOTE) WASHING CONDITION : AATCC 135:2015, TEST NO. (2)(III)A(ii); MACHINE WASH DELICATE CYCLE AT (41 ± 3) $\mathrm{^{\circ}C}$, TUMBLE DRY DELICATE.

05. APPEARANCE AFTER A WASHING (AATCC 135 : 2015, TEST NO. (2)(III)A(ii), MACHINE WASH DELICATE CYCLE AT (41 ± 3) C , TUMBLE DRY DELICATE)

	#1 ~ #4				
AFTER THE 10TH WASHING	THE BUBBLE WAS NOT FOUND.				

** End of The Report **

e-DOCUMENT SERVICE