

5F Annex Dragon Pearl Plaza
2123 Pudong Avenue
Shanghai 200135 - P.R. CHINA
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33

E-mail : ctcshanghai@ctcgroupe.com

Report No.: S181014268_1

08 November 2018

APPLICANT: CHANGZHOU SONGANCHENG CO.,LTD (C39276)

江苏常州市武进区牛塘镇卢西村查区1号
. CHANGZHOU
CHINA

侯建淮 / 13915090271@163.com

Date of receipt : 31 Oct. 2018
Testing period : 31 Oct. 2018
: 08 Nov. 2018

Buyer: —

Sample description: 手套

Reference no. : A18-10

Test(s) requested : —

Service : REGULAR

Brand / Section : —

Season : —

End use : 防割手套

Factory name : —

Factory code : —

For CE Marking : Yes

Previous report : —

Product category : —

Product type : —

Test stage : FIRST TEST

Supplier name : —


Exported to : —

1. Conclusion:

	Tests description	Conformity
	EN 388	
1	Abrasion resistance	Level 4
2	Blade cut resistance	Level 4
3	Tear resistance	Level 4
4	Puncture resistance	Level 3

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN
Laboratory Manager

Report No.: S181014268_1

08 November 2018

APPLICANT: CHANGZHOU SONGANCHENG CO., LTD (C39276)

2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
	GLOVE	palm	



181014268

Report No.: S181014268_1

08 November 2018

APPLICANT: CHANGZHOU SONGANCHENG CO., LTD (C39276)

3. GLOVE/

palm

	Method	Client Requirement	Unit	Result	Conformity
(+) 4. Abrasion resistance Number of cycles to breakthrough - Lowest value Performance Level	EN 388 : 2003		cycles	>8000 4	
(+) 4. Blade cut resistance I1 I2 I3 I4 I5 I _{mean} I1(2) I2(2) I3(2) I4(2) I5(2) I _{mean} (2) Performance level	EN 388 : 2003		Index	8.2 10.1 10.3 11.0 11.9 10.3 15.0 16.0 16.4 14.5 16.4 15.6 4	
(+) 4. Tear resistance Total torn tearing force - Lowest value Performance Level	EN 388 : 2003		N	>75 4	
(+) 4. Puncture resistance Force recorded - Lowest value Performance Level	EN 388 : 2003		N	141 3	

END OF TEST REPORT

(+)CNAS accreditation

Table of Performance Level for Glove

Test Item	Performance Level					
	0 ^{##}	1	2	3	4	5
Abrasion Resistance (EN 388) Number of cycles (minimum)	<100	100	500	2000	8000	---

Report No.: S181014268_1

08 November 2018

APPLICANT: CHANGZHOU SONGANCHENG CO., LTD (C39276)

Blade Cut Resistance (EN 388) Index (I) (minimum)	<1.2	1.2	2.5	5.0	10.0	20.0
Tear Resistance (EN 388) Force (N) (minimum)	<10	10	25	50	75	---
Puncture Resistance (EN 388) Force (N) (minimum)	<20	20	60	100	150	---

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard