

YOUR SELECTIONS & CHOICES

**Unsupported Neoprene
Gloves**

Neoprene (1)

Unsupported Neoprene Over
Latex (3)

Hand Protection

YOUR SELECTIONS: [🏠](#) [▶ HAND PROTECTION](#) [▶ CHEMICAL RESISTANT](#) [▶ UNSUPPORTED NEOPRENE GLOVES](#) [▶ NEOPRENE](#)

EN 374
AKL
EN 388
3121



[VIEW SPEC SHEET](#)

[REQUEST A SAMPLE](#)

Assurance®

Unsupported Neoprene, Flock Lined with Raised Diamond
Grip - 28 Mil

52-3665

- [DESCRIPTION](#)
- [DETAILS](#)
- [APPLICATIONS](#)
- [CHEMICALS](#)

CHEMICAL NAME	LEVEL	BTT
2-Butoxyethanol	3	63 MIN
2-Ethoxyethanol	5	58 MIN
2-Ethoxyethyl acetate	2	37 MIN

<u>2-Nitropropane</u>	1	26 MIN
<u>Acetaldehyde</u>	0	8 MIN
<u>Acetic acid, 99%</u>	4	152 MIN
<u>Acetone</u>	1	11 MIN
<u>Acetonitrile</u>	1	15 MIN
<u>Acrylic acid</u>	3	66 MIN
<u>Ammonium Fluoride, 40%</u>	6	>480 MIN
<u>Ammonium hydroxide</u>	5	>440 MIN
<u>Aniline (and homologs)</u>	3	69 MIN
<u>Aqua Regia</u>	6	>480 MIN
<u>Butyrolactone, 99%</u>	4	170 MIN
<u>Cirtic Acid, 10%</u>	6	>480 MIN
<u>Cyclohexanol</u>	5	392 MIN
<u>Diacetone alcohol</u>	3	96 MIN
<u>Dibutyl phthalate</u>	6	>480 MIN
<u>Dimethylformamide</u>	2	38 MIN
<u>Dimetyl Sulphoxide</u>	5	243 MIN
<u>Di-sec octyl phthalate</u>	6	>480 MIN
<u>Ethanolamine</u>	6	>480 MIN
<u>Ethyl acetate</u>	0	10 MIN
<u>Ethyl alcohol</u>	3	73 MIN
<u>Ethyl ether</u>	0	4 MIN
<u>Ethylene glycol</u>	6	>480 MIN
<u>Formaldehyde, 99%</u>	6	>480 MIN
<u>Formic acid</u>	6	>480 MIN
<u>Freon</u>	4	160 MIN
<u>Furfural</u>	2	35 MIN
<u>Hexamethyldisilazane</u>	4	153 MIN

<u>Hydrazine, 65%</u>	4	205 MIN
<u>Hydrogen chloride, 10%</u>	6	>480 MIN
<u>Hydrogen chloride, 37%</u>	5	>480 MIN
<u>Hydrogen fluoride, 48%</u>	6	>480 MIN
<u>Hydrogen peroxide, 30%</u>	6	>480 MIN
<u>Hydroquinone</u>	6	>480 MIN
<u>Isobutyl alcohol</u>	4	183 MIN
<u>Iso-octane</u>	3	92 MIN
<u>Isopropyl alcohol</u>	4	142 MIN
<u>Kerosene</u>	3	100 MIN
<u>Lactic acid, 85%</u>	6	>480 MIN
<u>Lauric acid, 36% in ethanol</u>	6	>480 MIN
<u>Maleic acid, saturated</u>	6	>480 MIN
<u>Methyl alcohol</u>	2	40 MIN
<u>Methyl Cellosolve®</u>	3	75 MIN
<u>Methylamine 40%</u>	3	79 MIN
<u>n-Butyl alcohol</u>	4	135 MIN
<u>n-Hexane</u>	1	16 MIN
<u>Nitric acid, 10%</u>	6	>480 MIN
<u>Nitric acid, 70%</u>	5	370 MIN
<u>Nitromethane</u>	1	22 MIN
<u>n-Pentane</u>	1	13 MIN
<u>n-Propyl alcohol</u>	3	75 MIN
<u>Octyl alcohol</u>	5	275 MIN
<u>Oleic Acid</u>	6	>480 MIN
<u>Oxalic acid, 12.5%</u>	6	>480 MIN
<u>Palmitic Acid, Sat</u>	6	>480 MIN
<u>Pentachlorophenol, 36% in Ethanol</u>	6	>480 MIN
<u>Perchloric acid, 60%</u>		>480 MIN

	6	
<u>Petroleum distillates (naphtha)</u>	1	15 MIN
<u>Phenol, 90%</u>	3	108 MIN
<u>Phosphoric acid, 85%</u>	6	>480 MIN
<u>Potassium hydroxide, 50%</u>	6	>480 MIN
<u>Sodium hydroxide, 50%</u>	6	>480 MIN
<u>Stoddard solvent</u>	3	62 MIN
<u>Sulfuric acid, 47%</u>	6	>480 MIN
<u>Sulfuric acid, 96%</u>	5	260 MIN
<u>Tannic Acid, 65%</u>	6	>480 MIN
<u>VM & P Naphtha</u>	2	35 MIN

CAUTION: This information is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This information should be used as a guide only.

SIMILAR ITEMS: Unsupported Neoprene Gloves



loading