

8th Generation Smart Tint® Technical Data Sheet

Description	NON-Adhesive Smart Tint®		Smart Cling® Self-Adhesive Smart Tint®	
	(HC-NF)	Low driving voltage High on clarity (LV-NF)	(HC-SF)	Low driving voltage High on clarity (LV-SF)
Film thickness	1 Mil.		1 Mil.	
Film sizes	71" x 1958" or 1800mm x 50m		71" x 1958" or 1800mm x 50m	
UV block	> 99%		> 99%	
IR block	Standard Low Haze High Clarity > 20%	IR90 Low Haze High Clarity + Heat Block > 98%	Standard Low Haze High Clarity > 20%	IR90 Low Haze High Clarity + Heat Block > 98
Solar heat gain coefficient (950 nm)	0.71	0.1	0.71	0.1
Operation temperature	- 10 °C ~ 60 °C			
Parallel light transmittance (650 nm)	96 ± 1 (on) 1.8 ± 0.5 (off)	98 ± 1 (on) 2 ± 1 (off)	96 ± 1 (on) 1.8 ± 0.5 (off)	98 ± 1 (on) 2 ± 1 (off)
Total light transmittance	90 ± 1 (on) 4 ± 2 (off)	98 ± 1 (on) 4 ± 2 (off)	90 ± 1 (on) 4 ± 2 (off)	98 ± 1 (on) 4 ± 2 (off)
Haze	3 ± 1 (on) 89 ± 2 (off)	3 ± 1 (on) 98 ± 2 (off)	3 ± 1 (on) 89 ± 2 (off)	3 ± 1 (on) 98 ± 2 (off)
Operating voltage	28 ~ 60 VAC	28 ~ 60 VAC	28 ~ 60 VAC	28 ~ 60 VAC
Frequency range	50 ~ 60 Hz			
Power consumption	3 ~ 4 W/m ²			
Switching speed	Off → On : 50~100 milliseconds / On → Off : 200~300 milliseconds			

※ HC= USA/CANADA Line Voltage LV= Low Voltage

Tinsel Strength Tested - 14,000 lbs. per sq inch



SMART CLING®
Technology

A clear leap above the traditional self adhesives