

Product Details

Format	1 Strip Plank	EN ISO 24342
Finish	Wood Look	
Profile	Click System	
Edge Profile	Bevelled	
Thickness	6mm	EN ISO 24346
Width	190mm	≤0.10 mm
Length	1320mm	
Wear Layer	0.55mm	EN ISO 24340
Pack Size	1.99m ² /box	8pcs/box
Weight	17.59 kg	EN ISO 23997

Installation & Maintenance

Floated Installation	Yes (recommended option)
Fully Bonded	Yes
Waterproof	Yes
Nailed	No
Recyclable	100%

LRV Ratings

Name:	LRV:
Basalt	14.91
Dacite	34.95
Skarn	32
Gabbro	17
Flint	24
Willow	32.90
Adler	26
Edson	37.15
Hinton	40
Firwood	21

Installation & Warranty

All Plusfloor floors must be installed by a competent installer who will have the necessary skills and take individual site circumstances into account. Plusfloor's warranty will apply only to floors which have been installed by a competent flooring installer comparable to BS8201 in the UK or equivalent standard worldwide.

© This technical data sheet was written by Plusfloor, Carnforth Business Park, Oakwood Way, Carnforth, Lancashire, LA5 9FD. At the time of writing and publication of this folder, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties.

Technical Criteria

Origin	Europe
Level of use	EN ISO 10874
Inflammability	EN 13501 Bfl-S1
Scratch resistance	EN ISO 660-2 Class T
Squareness	EN ISO 24342 ≤ 0.20 mm
Straightness	EN ISO 24342a ≤ 0.30 mm
Slip Resistance	EN 13893 DS
Slip Resistant	DIN 51130 R10
Residual indentation	EN ISO 24343-1 ≤ 0.10 mm
Furniture leg resistance	EN ISO 16581 No cracks
Curling	EN ISO 23999 ≤ 1.5 mm
Dimensional stability	EN ISO 23999 Norm ≤ 0.25 %
Thermal resistance R	EN 12664 0.025 m ² .K/W
Formaldehyde group	EN 717-1 E1
Acoustic insulation	EN ISO 717-2 21 dB
Castor chair resistance	EN ISO 4918 No damage
Stain resistance	EN ISO 26987 Very good
Light fastness	EN ISO 105-B02 ≥6
Underfloor heating	EN 12524 Suitable, max 27°C
Warranty (year)	20 Residential 10 Commercial

The warranty covers manufacturing defects and premature wear in the event of normal use.