

Soudasil HT1



- 100% RTV Silicone
- High Temp Silicone, Withstands Temperatures Up to Intermittent Heat of 500°F
- Red In Colour
- Excellent Adhesion to Glass, Ceramic, Porcelain, Metals, Wood & Many More
- Permanently Elastic
- Watertight & Airtight
- Easy to Apply & Easy Clean-up
- UV Resistant
- Meets ASTM C-920, Type S, Grade NS, Class 25
Complies With FDA Regulations 21 CFR Section 177.2600: "Rubber Articles Intended For Repeated Use"

HVAC/R Heating Elements Vents & Pipes



This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third-party intellectual property rights, especially patent rights. SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT, OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.

Soudasil HT1



Base	Polysiloxane	
Sag	No sag in vertical displ. @49°C	ASTM C 639
Curing system	Moisture Cure	
Skin Formation (*)	6 - 7 minutes	@ 24°C & 50% relative humidity
Tack-free time (*)	25 minutes	ASTM C679
Curing time (*)	48 hrs, 1/4" diameter bead	@ 24°C & 50% relative humidity
Hardness - Shore A	20 +/- 5	ASTM C661
Tensile Yield	170 psi	ASTM D412
Elongation	>350%	ASTM D412
Movement capability	+/-25%	ASTM C719
Stain and color change	Passes	ASTM C510 (mortar)
Artificial weathering	No Cracking	ASTM C793
Service temperature range	-40 °C to +260 °C	
Application temperature range	-37 °C to +60 °C	
Shelf life	12 months	Stored between +5 °C à +25 °C
VOC	3% - 30g/L	Directive 2004/42/EG

(*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Limitations:

- This product is not paintable.
- This product is not to be used as a structural glazing sealant.
- We always recommend a preliminary adhesion test on every surface.
- Lower temperatures and humidity will extend curing time.

CAUTION:

KEEP OUT OF REACH OF CHILDREN. Avoid skin and eye contact. On contact, uncured sealant could cause irritation to skin and eyes. In case of eye contact, flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed, do not induce vomiting, call a physician. Soudasil HT1 is manufactured for professional use only. Refer to Safety Data Sheet (SDS) for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT