BIYORK HydroGen 6 Technical Data										
Plank Size (Length x Width x Height)		Bevel	Finish	Underlayment	Gloss Level	Installation	Overall Thickness	Wear Layer Thickness	Radiant Heat	
1220mm*180mm*6.0mm 600mm*300mm*6.0mm		Microbevel	Antique Wood Texture/Slate Texture	HD IXPE 1mm	5-7°	Click Floating	6.0mm	0.5mm	Approved for water(temperature≤50C) based radiant heat systems	
WARRANTY: Residential Commercial		Planks/ Carton	Coverage/				Carton Weight	Cartons/ Pallet	PALLET: Coverage/ Pallet sqft	
30years	10years	10	Carton 23.64sqft		ength x Width x He 30mm X 189mm X		22kg/18.5kg	45/54	1064 sqft/1047 sqft	
Soycars	10/013	10	19.38sqft 610mm X 309mm X 6			53mm		45/54	1004 3417/1047 3417	
TESTING:										
Reference			ASTM Norms			Test Request		Result		
Expansion After Exposure to Heat (50°C)			ASTM F2199-09			≤ 0.6mm/m		Pass		
Impact sound reduction (IIC)			ASTM E492-09			Based on actual data		IIC=72		
STC rating			ASTM E90-09			Based on actual data		STC=68		
			ASTM Norms			Test Request		Result		
Determination of Thickness:			ASTM F387 - 17			Tmax-Tmin≤0.5mm, ∆Tavg: ≤0.5mm		Pass		
Determination of Squareness:			ASTM F2055 - 17			Qmax≤0.25mm		Pass		
Determination of Straightness:						Smax≤0.25mm		Pass		
Thickness,wear layer			ASTM F410			0.011 in. (0.27 mm) minimum		Pass		
Resistance to heat			ASTM F1514			ASTM F1700, 6.9 Not greater than 8.0 after 7 day exposure to 158°F (70°C)		Pass		
Resistance to light			ASTM F1515			ASTM F1700, 6.10 Not greater than 8.0 after a 300 hour exposure		Pass		
Residual indentation			ASTM F1914			Residual Indentation ≤ 8%		Pass		
Formaldehyde Emission:			ASTM D6007 - 14			Follow Test Report		Not Detected		
Residual Indentation Static Load:			ASTM F970-17			250 psi, ≤ 0.005 inch		Pass		
Castor Chair Resistance:			NALFA LF 01-2011			No visible damage		No visible damage		
Wear Resistance:			ASTM D4060 - 19			Follow Test Report		Pass		
Dimens	Dimensional Stability and Curling:			ASTM F2199-09			Max : MD&CD : 1.67mm/m 2 Curling: 2.0mm		Pass	
Classification of S	Classification of Smoke Development (Flammability Test):			ASTM E 648-10			Follow Test Report		Class I	
Vertical Burning			UL 94-2013			Follow Test Report		V-0		
	Slip Resistance:			ASTM C1028-07			Follow Test Report		Pass	
	Peel Resistance:			ISO 24345-2006			X Direction: 100N/50mm, Y Direction 75N/50mm		Pass	
Res	Resistance to Chemicals:			ASTM F925-13			Slight Change maximum in Surface Dulling, Surface Attack, or Staining		Rating 0: No Change	
S	Soluble Heavy Metal:			ASTM F963			≤100PPM		Pass	
VOC			FLOOR SCORE			PASS		Pass		
Dimensional Stability of Resilient Floor Tile after Exposure to Heat			ASTM F2055			Squareness = 0.010 inch (0.25 mm) maximum, Size and Tolerance = + 0.016 inch/linear foot (0.4 mm/305 mm)		Pass		
Phthalate			ASTM F963			≤1000PPM		Not Detected (≤60PPM)		

www.BIYORKCANADA.COM

Biyork product specifications are subject to change. Please always refer to a physical sample for reference. All rights reserved 2020.