

# THE MARIGOLD COLLECTION

AVAILABLE SIZES & TILE BODIES:  
12x12 POLAR ICE TERRAZZO  
CONTACT US FOR CURRENT LEAD TIMES



## SERIES: ARCHES



BLUE VELVET



CREAMSICLE



CRIMSON



FOREST



ROSE GOLD



SHERBERT



WATERMELON

## SERIES: PETALS



BLUE VELVET



CREAMSICLE



CRIMSON



FOREST



ROSE GOLD



SHERBERT



WATERMELON

### APPROVED INSTALLATION SPACES

- INTERMITTENT WET SPACES
- INTERIOR WALL APPLICATIONS
- LIGHT TRAFFIC RESIDENTIAL FLOORING
- COMMERCIAL WALLS

### NOT RECOMMENDED INSTALLATION SPACES

- SUBMERGED WATER APPLICATIONS (POOLS, FOUNTAINS)
- SHOWER FLOORS
- STEAM SHOWERS OR SAUNAS
- OUTDOOR SPACES
- COMMERCIAL FLOORS

## SEALANT PERFORMANCE CHARACTERISTICS

|   |   |
|---|---|
| Substrate Tested:                               | Steel   |
| Surface Preparation:                            | Wash with water based biodegradeable neutral cleaner          |
| Application:                                    | Direct to surface   |
| Tensile Adhesion:<br>(ASTM D4541)               | 1600 - 1800 psi   |
| Abrasian Resistance:<br>(ASTM D4060)            | 33 mg loss  |
| Condensing Humidity 1000 Hours:<br>(ASTM D2247) | Rusting: None<br>Blistering: None                             |
| Impact Resistance:<br>(ASTM D2794)              | 160 in-lbs.   |
| Flexibility - Conical Bend:<br>(ASTM D522)      | % Elongation: >32%<br>Resistance to Crackings: <1/8" diameter |
| Pencil Hardness:<br>(ASTM D3363)                | Scratch: 2H<br>Gouge : 3H                                     |
| MEK Double Rubs:<br>(Internal Testing)          | 1000+   |
| Salt Fog 1000 Hours:<br>(ASTM B117)             | Rusting: 10 (None)<br>Scribe Undercutting: <0.5 mm            |
| Water Vapor Transmission:<br>(ASTM E96)         | 2.4 perms   |
| QUV 1000 Hours:<br>(ASTM D4587)                 | Passed SSPC Paint 36 Standard of:                             |
| Color Change:                                   | Less than 2.0 Delta E Change                                  |
| Gloss Change:                                   | Less than 30 Gloss Change                                     |
| Flame Developed:<br>(ASTM 84)                   | 10 - Class A  |
| Smoke Spread:<br>(ASTM 84)                      | 5 - Class A   |

## CARE AND MAINTENANCE

- CLEAN WITH A SOFT CLOTH, WARM WATER, AND NON-ACIDIC SOAP OR A PH NEUTRAL STONE CLEANER.
- TILE SURFACES SHOULD BE PROTECTED FROM SCRATCHES.
- AVOID ANY CARE PRODUCTS THAT CONTAIN THE FOLLOWING: ABRASIVES, PHOSPHORIC ACIDS, SCOURING POWDERS, CHLORINE, ACETONE, OR GLYCOLIC ACIDS. AVOID BRUSHES AND SCOURING PADS.
- NEVER USE AN ELECTRIC SCRUBBER OR BUFFER, ROTARY TOOLS, ETC. ON PRODUCT.
- PRODUCT SHOULD BE RESEALED ON A REGULAR BASIS. FOLLOW MAINTENANCE SCHEDULE RECOMMENDED BY SEALER MANUFACTURER.