

DEKORCRYL KIT

SURFACE VOID FILLER KIT



DekorCryl is an acrylic co-polymer emulsion, specifically formulated as an additive for void-sealer slurry coats used for sealing porous, bituminous substrates in preparation for the application of DekorGrip resin bond coats. The DekorCryl Kit now comes packed with all the ingredients ready to mix, removing the requirement to obtain additional materials prior to application.

FEATURES & BENEFITS:


- No need for additional materials
- Consistent slurry mixture
- Faster curing time
- Helps to prevent bleeding of bitumen
- Once laid, the void filler helps to maintain correct coverage of resin
- Ensures a better consistent final finish to product applied on top



Beige



CONTACT US TO FIND OUT MORE OR BOOK A DEMONSTRATION WITH OUR TECHNICAL EXPERTS.

 CALL FREE: 0808 118 1922

 MEONUK.COM



MEON
DELIVERING GREAT SURFACES

PREPARATION:

SURFACE PREPARATION:

All surfaces to be sealed should be thoroughly clean and dry. Any oil contamination should be thoroughly washed away using a mild detergent.

Use **Meon Gaffer Tape** to mask out giving you a neat, crisp finished edge.

MIXING:

MIXING INSTRUCTIONS:

Open the outer carton and remove kit contents. Open the Meon Dekorcryl liquid compound and stir well using the mixing stick supplied.

Pour the liquid compound into outer bucket and slowly add the powder

compound - for best results continuous mixing is recommended. Mix for approximately 3 minutes on a low speed with the **Meon Collomix twin handle mixing drill**.

APPLICATION:

The slurry mixture is poured on to the surface and spread evenly using a flat squeegee, forcing the material into the surface texture and leaving a membrane of no more than 1mm over the surface. If you have masked out with **Meon Gaffer Tape** ensure you remove no longer than 10-15 minutes after application.

Temperature of application: Recommended surface temperature during application should be between 5°C and 30°C.

Do not apply when the air or surface temperature is below 5°C or less than 3°C above dew point, or if this is likely to occur during the curing period.

Do not apply when there is rain, mist, fog, or snow imminent; when humidity is high or the surface is wet with condensation or likely to be during the drying period.

CURING:

DRYING TIMES:

The drying time of DekorCryl Void Filler Kit takes approximately 2 hours in a warm dry atmosphere. As the material is an emulsion, humidity will greatly affect the drying time and heavy rain will wash any newly laid material away.

The DekorCryl system needs to be fully cured (being hard to touch and with no evidence of any damp patches) prior to the application of resins.

TECHNICAL:

COVERAGE:

5-10m² per 20kg kit depending on macrotexture depth of the surface.

AFTERCARE AND MAINTENANCE:

After use, clean all tools using clean water.

PACKAGING AND STORAGE:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5 and 20°C.

SHELF LIFE:

6 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

Supplied in 20kg kits.

HEALTH AND SAFETY:

Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.

MEON UK

+44 (0)23 9220 0606
MAIL@MEONUK.COM
MEONUK.COM

MEON IRELAND

+353 (0)1 840 7647
INFO@MEONIRELAND.COM
MEON.IE



MEON
DELIVERING GREAT SURFACES