

HARDMASTER W675

FAST SETTING MORTAR REPAIR



HardMaster W675 is a high-performance, fast-setting, multipurpose concrete repair material and non-shrink grout that is ideal where rapid strength, durability and low shrinkage are desired. Can be used indoors and outdoors, also in wet areas, applied using similar methods to cement based materials. Use HardMaster W675 for general and structural concrete repair, doweling and anchoring, industrial grouting, formed work, vertical and horizontal trowel applications. HardMaster W675 is ideal for airport, highway, industrial and marine applications.

FEATURES AND BENEFITS

- High-Strength - 3 times stronger than most concrete
- Fast - Sets in 15 minutes, structural strength in 1 hour
- Durable - formulated for long life in critical applications
- High resistance against many chemicals
- Excellent bond directly without bonding compound
- Structural for repairs and new construction



Grey



CONTACT US TO FIND OUT MORE OR BOOK A
DEMONSTRATION WITH OUR TECHNICAL EXPERTS.

CALL FREE: 0808 118 1922

MEONUK.COM



MEON
DELIVERING GREAT SURFACES

COMPOSITION:

HardMaster W675 is a high-performance blend of rapid setting cement and special mineral aggregates. HardMaster W675 is non-metallic, without chlorides. HardMaster W675 is similar in appearance to Portland cement repair materials and may be applied using similar methods.

PREPARATION:

SUBSTRATE PREPARATION:

For repairs, application surface shall be clean, sound and free from any materials that may inhibit bond, such as oil, asphalt, curing compound, acid, dirt and loose debris. Roughen surface and remove all unsound material. Apply HardMaster W675 to a surface that is thoroughly saturated with no standing water.

MIXING:

MIXING INSTRUCTIONS:

The use of an **Meon OX Pro Rubber Blade Mixing Paddle** coupled with a twin handled mixing unit is recommended. Organize work so that all personnel and equipment / tools are in place before mixing. HardMaster W675 is mixed with 560ml to 940ml clean water per 5 kg bucket. Use less water to achieve higher strength values. Do not exceed the maximum water admixture of 940ml per 5 kg bucket. Place water into the mixing container and add HardMaster while the stirrer is running. To achieve a uniform consistency, mix for 1 to 3 minutes.

DO NOT re-temper mixed material.

APPLICATION:

Apply HardMaster W675 using traditional construction methods in thicknesses from featheredge to 100mm. For heavy loads and vehicle traffic, minimum thickness will vary. Not intended for high heat applications above 150°C. For deeper sections, bulk up mix with clean 10mm aggregate up to 30% by weight. For overlay applications, a minimum of one test section should be prepared to evaluate the suitability of the materials and procedures.

Do not apply HardMaster at sub-base or environmental temperature below +5°C. Temperatures above 20°C will reduce the working time.

Recommended ambient application temperature is 5°C to 25°C.

CURING:

Begin water curing as soon as the surface has lost its moist sheen. Keep exposed surfaces wet for a minimum of 1 hour until the product has achieved sufficient strength. When experiencing extended setting times, due to cold temperature or the use of a retarder, longer cure times may be required.

TECHNICAL:

PERFORMANCE DATA:

Layer thickness	0 - 100 mm
Approx. Coverage	0.05m ² @ 50mm / 5kg kit
Initial set	after 15 min.
Ready for traffic	after 60 min.
COMPRESSIVE STRENGTH	
after 60 min.	> 20,0 N/mm
after 180 min.	> 31,0 N/mm
after 7 days	> 41,0 N/mm
after 28 days	> 62,0 N/mm
Modulus of elasticity	38.240 N/mm
Sulfate resistance	yes
Frost/deicer resistance	yes
Penetration behaviour	yes
Packaging	5kg

Technical Data @ +20°C and 65% relative air humidity

STORAGE AND PACKAGING:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5°C & 20°C.

SHELF LIFE:

12 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

5kg kit in a bucket.

HEALTH AND SAFETY:

These products contain cement and have an alkaline reaction with moisture/water. Therefore protect hands and eyes. In case of contact with eyes consult a doctor. Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.

MEON UK

+44 (0)23 9220 0606
 MAIL@MEONUK.COM
 MEONUK.COM

MEON IRELAND

+353 (0)1 840 7647
 INFO@MEONIRELAND.COM
 MEON.IE



MEON
 DELIVERING GREAT SURFACES