

ULTRACRACK L270

MMA OVERBANDING & CRACK REPAIR KIT



UltraCrack L270 is a methyl-methacrylate (MMA) cold plastic product designed for crack infill and overbanding. As with all MMA products, it is very fast-curing making it ideal for live traffic situations where road closure time needs to be kept to a minimum. Very durable, enabling permanent repairs which will extend the life of surfaces by resisting the inflow of water and minimising damage caused by freeze/thaw.

UltraCrack L270 is a cold-lay system, requiring no hot works or specialised equipment; along with its simple application method, this puts the product within the reach of any competent install team. This allows the best use of human resources and enables a rapid response to any reactive works, without the cost or lead-in times associated with specialist subcontractors It is suitable for any asphalt surface, including roads and highways, pavements, airfields, station platforms.

FEATURES AND BENEFITS

- · Fast curing allows traffic within minutes of minimum disruption on site
- Strong and durable resistant to wear
- Skid resistant good skid resistance that can be optionally increased if required
- · Safe applied with no hot works or big equipment
- · Cost effective reduces defect costs and obviates specialist call out charges





CONTACT US TO FIND OUT MORE OR BOOK A DEMONSTRATION WITH OUR TECHNICAL EXPERTS.



CALL FREE: 0808 118 1922





PREPARATION:

SURFACE PREPARATION:

UltraCrack L270 is designed for use on asphalt surfaces only. The application surface should be dry, sound and clean, free from grease, oil, rust, scale, dirt, or any other soiling that might affect adhesion or performance.

MIXING:

MIXING INSTRUCTIONS:

First stir the base resin, then thoroughly mix the bag of catalyst powder into the resin with a mechanical mixer, ensuring the powder has fully mixed throughout, and stir for 30 seconds. Once mixed, it is recommended to leave the resin and catalyst for 1-2 minutes to allow the catalyst to dissolve. Please note that the product will start to cure rapidly after mixing! In warmer conditions, it is acceptable to reduce the amount of catalyst powder added, by up to 25%. This will slow the curing process.

THINNING:

Do Not thin.

APPLICATION:

Lay the UltraCrack L270 using a hand-mould - we recommend a **Meon Hand Mould with Funnel 40 x 100mm** for ease of use. Pour the UltraCrack L270 into the mould using a jug and extrude the product along the line of the joint of crack.

For higher level of skid resistance value (SRV), overscatter the product immediately with 1-2mm grey bauxite supplied with the kit.

Do not apply when the air or surface temperature is below 5°C or less than 3°C above dew point, or if this is likely to occur during the curing period.

Do not apply when there is rain, mist, fog, or snow imminent; when humidity is high or the surface is wet with condensation or likely to be during the drying period.

CURING:

Potlife: 5 -10 minutes at 15°C Touch dry: 15 minutes at 15°C Traffic time: 50 minutes at 15°C

TECHNICAL:

COVERAGE:

Approx. '10m of 40mm x 1.5mm, per kg

AFTERCARE AND MAINTENANCE:

Uncured UltraCrack L270 should be cleaned from tools and equipment using **Meon UltraClean X795**.

STORAGE AND PACKAGING:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5°C and 20°C .

SHELF LIFE:

Minimum 12 months when stored under cover, in original unopened boxes, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

9kg and 18kg kits.

HEALTH AND SAFETY:

Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.







MEONUK.COM

MEON IRELAND

() + 353 (0)1 840 7647



MEON.IE

