

ECHOSTAR 25 GLASS BEADS

1180-212 μ m TYPE 2 GLASS BEADS




The Echostar 25 glass beads are high performance beads with a very high physical and chemical resistance and have excellent retro-reflectivity due to a high quality manufacturing process ensuring over 80% bead roundness. Echostar 25 is a Type 2 bead which is designed to provide retro-reflectivity in both wet and dry conditions. The Echostar 25 beads are 1180-212 μ m which is suitable for use on line marking material applications of at least 590 μ m DFT. The beads are CE marked according to EN 1423.

FEATURES AND BENEFITS

- High retro-reflectivity - over 80% roundness
- Suitable for use on applications at least 590 μ m
- Coatings available for a range of line marking products



CONTACT US TO FIND OUT MORE OR BOOK A
DEMONSTRATION WITH OUR TECHNICAL EXPERTS.

 CALL FREE: 0808 118 1922

 MEONUK.COM



MEON
DELIVERING GREAT SURFACES

APPLICATION:

Application should be made at a temperature no lower than 5°C. These beads must be applied immediately after the product has been applied, with suitable equipment. For best performance we recommend using a pressurised bead system to apply the beads. The dosage rate for type 2 beads is typically 400-1000g/m², however dosage rates do vary depending on what product the beads are being applied onto, refer to the relevant product technical data sheet for further dosage recommendations.

TECHNICAL:

PARTICLE SIZE DISTRIBUTION:		1180-212µm
Sieve (µm)	Accumulated retainment (%)	
1400	0-2	
1180	0-10	
1000	0-10	
850	15-50	
710	15-50	
600	50-90	
500	50-90	
425	80-100	
355	80-100	
300	90-100	
250	90-100	
212	95-100	

Chemical composition: Soda lime glass
 Roundness: >80%
 Refractive index: Class A >1.5
 Physical and Chemical resistance: In accordance to EN 1423

AFTERCARE AND MAINTENANCE:

Sweep up excess beads and dispose of suitably.

STORAGE AND PACKAGING:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5°C & 20°C.

SHELF LIFE:

12 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

Supplied in 25kg bags.

HEALTH AND SAFETY:

Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.

CHOOSING THE RIGHT BEAD:

There are two key considerations when choosing what glass bead to use. These are the bead size and the bead coating. Echostar 25 beads are 1180-212µm which are suitable for applications at least 590µm dry film thickness (DFT). Glass bead coatings affect both the adhesion and the flotation of the bead. It is important to use a bead coating which is designed for use with the product being applied otherwise the beads will not adhere or sink adequately into the product. The below table sets out which bead coating is compatible with each type of product:

PRODUCT TYPE	COATING TYPE	FULL NAME
Cold Plastic	BCP	Echostar 25 BCP Type 2 Glass Beads

Echostar 25 Beads are available as an anti-slip mix called SRT, for example: Echostar 25 BCP SRT Type 2 Glass Beads.

MEON UK

+44 (0)23 9220 0606
 MAIL@MEONUK.COM
 MEONUK.COM

MEON IRELAND

+353 (0)1 840 7647
 INFO@MEONIRELAND.COM
 MEON.IE



MEON
 DELIVERING GREAT SURFACES