

ULTRALINE L210


MMA LINE MARKING PAINT



Spectrum UltraLine L210 is a methyl-methacrylate (MMA) cold plastic for line markings. UltraLine L210 consistently outperforms traditional thermoplastic as it is extremely hardwearing and has excellent adhesion to asphalt and concrete surfaces. It can be applied by hand or using specialist application equipment for larger applications. UltraLine L210 is ideal for any transverse markings or high wear areas such as roundabouts and junctions.

BENEFITS & FEATURES

- Very hard wearing - lasts at least 3 times as long as thermoplastic
- Very fast cure time to allow rapid re-opening of areas to traffic
- Excellent adhesion to asphalt and concrete
- BSI approved for highway use
- Solvent-free formula



CONTACT US TO FIND OUT MORE OR BOOK A DEMONSTRATION WITH OUR TECHNICAL EXPERTS.

CALL FREE: 0808 118 1922

MEONUK.COM



MEON
DELIVERING GREAT SURFACES

PREPARATION:

SURFACE PREPARATION:

The application surface should be sound and clean, free from grease, oil, rust, scale, dirt, or any other soiling that might affect adhesion or performance. In any case, but especially in the case of overcoating existing line markings, it is further recommended that test areas be coated to ensure good adhesion and/or compatibility with the substrate.

Asphalt - weathered - it is recommended that asphalt and other similar surfaces be allowed to thoroughly harden for up to 2 months before painting. Test trials should be carried out in the first instance on a small area.

Asphalt - new - whilst we do not recommend coating new surfaces, we appreciate that it often has to happen. There is a risk of bitumen "bleed" through the line; if this happens we recommend either priming the area with **Meon UltraNuvo** asphalt primer, **Meon ViaLine F210**, or laying a thin coating of UltraLine L210, allowing to cure and then laying a 2nd full coat on top, as the bleed is usually contained within the first coat.

Concrete and other cementitious surfaces, including tamped or brushed concrete - we recommend a preparation method suitable for the specific location and surface is carried out before application of product, to ensure surface is properly prepared back to clean and sound substrate. It is critical that utmost attention is paid to cleanliness and good workmanship, whatever preparation method is used, as the presence of any loose material, dust, soiling or previous coatings are likely to reduce adhesion of new coatings. New concrete should be left to harden before coating, as the curing process and residual moisture content can lead to product delamination if coated too early. We always recommend priming concrete with **Meon UniPrime X250**.

MIXING:

MIXING INSTRUCTIONS:

It is essential that UltraLine L210 is properly mixed using mixing paddle and drill, or similar. The resin component should be stirred thoroughly, then mix the catalyst component into the base component, for minimum of 90 seconds. If the product is not properly mixed it is likely that the chemical reaction will be impeded and the product may not perform properly.

THINNING:

This product must not be thinned.

APPLICATION:

We recommend the use of hand moulds to extrude the product. Rollers can be also be used for larger areas such as zebra crossings and stop lines. Alternatively, special application equipment can be used to machine apply - contact Meon for more information. We recommend applying reflective glass beads to all line markings using UltraLine L210. Beads must be applied as soon as possible after application, before the product 'skins' over. We recommend either **Echostar 10 BCP Reflective beads** or **Standard Highway Grade 600Qm AC05 Beads** for a Type I marking. For a Type II marking use the **Echostar 25 BCP Reflective beads**.

CURING:

Touch dry: 5 minutes @ 15°C
 Walk on time: 15 minutes @ 15°C
 Traffic time: 25 minutes @ 15°C

TECHNICAL:

COVERAGE:

Area: 0.4m² per kg
 Linear: 4m of 100mm line per kg
 (approx. 30m of 100mm line per tin)
 WFT: 1000 microns

CERTIFICATION: (manufactured to BS:EN1436)

Test	Class
Luminance	B0
Colour (x)	White
Colour (y)	White
RL Dry (mcd/m ² /lx)	R4
RL Wet (mcd/m ² /lx)	RW0
Skid Resistance	S2
Qd (mcd/m ² /lx)	Q3

AFTERCARE AND MAINTAINENCE:

Use **Meon UltraClean X795** to clean uncured UltraLine L210 from tools and equipment. Lines can be maintained by cleaning with clean water or mild detergent solution.

STORAGE AND PACKAGING:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5 & 20°C. If product is stored for more than 30 days, full and thorough mechanical mixing will be required before using.

SHELF LIFE:

12 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

Supplied in 8kg tins.

HEALTH AND SAFETY:

Avoid inhalation of vapours and contact with skin and eyes. Wear suitable protective clothing, gloves and eye/face protection. Take additional care when spraying under high pressure. Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.

MEON UK

+44 (0)23 9220 0606
 MAIL@MEONUK.COM
 MEONUK.COM

MEON IRELAND

+353 (0)1 840 7647
 INFO@MEONIRELAND.COM
 MEON.IE



MEON
 DELIVERING GREAT SURFACES