


ULTRAGRIP L240

MMA SLIP RESISTANT COATING



FEATURES:

- · Fast cure time
- · Very hard wearing
- · Large colour range available
- High SRV

BENEFITS:

- · Quick return to service
- · Long lasting solution
- · Options for a range of applications
- Increased safety over lifetime



Jet Black RAL 9005











Other Colours

CONTACT US TO FIND OUT MORE OR BOOK A <u>DEMONSTRA</u>TION WITH OUR TECHNICAL EXPERTS.







PREPARATION:

SURFACE PREPARATION:

The application surface should be sound and clean, free from grease, oil, rust, scale, dirt, or any other soiling that might affect adhesion or performance. In any case, but especially in the case of overcoating existing surface coatings, it is further recommended that test areas be coated to ensure good adhesion and/or compatibility with the substrate.

Tarmacadam - weathered - it is recommended that asphalt and other similar surfaces be allowed to through harden for up to 2 months before painting unless primed. Test trials should be carried out in the first instance on a small area.

Concrete and other cementitious surfaces – including powerfloat, tamped or brushed concrete, monoblocks & pavers – Ensure surface is sound, clean and free from laitance – we recommend a preparation method suitable for the specific location and surface is carried out before application of product, to ensure surface is properly prepared back to clean and sound substrate.

Examples of preparation methods that may be suitable are captive shot blasting, diamond grinding, scabbling or planing. It is critical that utmost attention is paid to cleanliness and good workmanship, whatever preparation method is used, as the presence of any loose material, dust, soiling or previous coatings are likely to reduce adhesion of new coatings.

New concrete should be left to harden before coating, as the curing process and residual moisture content can lead to product delamination if coated too early.

PRIMERS:

Weathered asphalt & tarmacadam - no primer required

New asphalt & tarmacadam up to 2 months - use **Meon UniPrime**L257 primer.

Concrete, pavers & monoblocks - use Meon UniPrime L251 primer.

VOID FILLING:

Substrate with macrotexture over 1.0mm - use Meon ScratchCote

MIXING:

MIXING INSTRUCTIONS:

Stir the resin component thoroughly slowly adding the aggregate supplied. Then add the appropriate amount of catalyst and continue mixing with a slow-speed stirrer until the mixture is consistent and apply immediately.

THINNING:

This product is supplied ready to use and must not be thinned.

APPLICATION:

Pour the mixed product onto the surface and spread evenly using a **4mm serrated squeegee**. Backroll to provide an even surface - a short pile roller will give a slightly finer finish and a medium pile will give a more textured finish. It is important that care is taken to roll evenly and in the same direction, to provide an even appearance. Do not apply when the air or surface temperature is below 5°C or less than 3°C above dew point, or if this is likely to occur during the curing period.

CURING:

Pot Life	Touch Dry	Full Cure
5-10 minutes	5 minutes	1 hour

Technical data @ 15°C and 65% relative humidity

TECHNICAL:

Typical Coverage:	m² per kg	g/m²	m² per kit
	0.46m²	2.16kg	9m²
Film Thickness:	WFT	DFT	
	1200	1200	
SRV:	60		
Certification:	Typically performs to excess of 400,000 wheel passes.		

AFTERCARE AND MAINTENANCE:

Use **Meon UltraClean X795** to clean tools and equipment after application. Once laid, UltraGrip L240 will be naturally cleansed by rainfall. This process can be replicated using soft brush and mild detergent if required.

STORAGE AND PACKAGING:

STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5°C & 20°C. If product is stored for more than 30 days, full and thorough mechanical mixing will be required before using.

SHELF LIFE:

6 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

SIZES AVAILABLE:

Supplied in 20kg kits, consisting of 18kg resin plus 2kg aggregate.

HEALTH AND SAFETY:

Avoid inhalation of vapours and contact with skin and eyes. Wear suitable protective clothing, gloves and eye/face protection. Take additional care when spraying under high pressure. Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on 023 9220 0606.

MEON UK





MEONUK.COM

MEON IRELAND

(+ 353 (0)1 840 7647

■ INFO@MEONIRELAND.COM

MEON.IE

