

# VERSALINE W210

## WATER BASED ACRYLIC LINING PAINT



Spectrum VersaLine is a high solids, fast-drying waterbased traffic paint formulated specifically for airless spray equipment. VersaLine provides a viable alternative to the use of solvent based products and has been developed in close collaboration with airless spray machine users, to overcome traditional problems of spraying waterbased products using airless systems. Spectrum VersaLine has high opacity and good coverage rates, making it ideal for use on highways, docks, airfields and carparks; it is also widely used in food preparation and storage areas.


The waterbased formulation removes the need for solvent thinner handling, storage and disposal. Can be oversealed for internal floors where gloss finish is required to minimise soiling.

### BENEFITS & FEATURES

- Removes requirement for solvent thinners
- Non-hazardous product
- Non-flammable
- Fast drying for rapid return to traffic



Yellow



White



Black



Red



CONTACT US TO FIND OUT MORE OR BOOK A DEMONSTRATION WITH OUR TECHNICAL EXPERTS.

CALL FREE: 0808 118 1922

MEONUK.COM



**MEON**  
DELIVERING GREAT SURFACES

## PREPARATION:

### SURFACE PREPARATION:

The application surface should be sound and clean, free from grease, oil, rust, scale, dirt, or any other soiling that might affect adhesion or performance. In any case, but especially in the case of overcoating existing line markings, it is further recommended that test areas be coated to ensure good adhesion and/or compatibility with the substrate/previously applied coatings.

**Tarmacadam** - weathered - It is recommended that asphalt and other similar surfaces be allowed to through harden for up to 6 months before painting. Test trials should be carried out in the first instance on a small area.

**Concrete** & other cementitious surfaces - including powerfloat, tamped or brushed concrete, monoblocks & pavers - Ensure surface is sound, clean and free from laitance - we recommend a preparation method suitable for the specific location and surface is carried out before application of product, to ensure surface is properly prepared back to clean and sound substrate.

Examples of preparation methods that may be suitable are captive shot blasting, diamond grinding, scabbling or planing. It is critical that utmost attention is paid to cleanliness and good workmanship, whatever preparation method is used, as the presence of any loose material, dust, soiling or previous coatings are likely to reduce adhesion of new coatings.

**New concrete** should be left to harden before coating, as the curing process and residual moisture content can lead to product delamination if coated too early.

### PRIMERS:

Not generally required but a thinned first coat can be used if surface is particularly absorbent.

## MIXING:

### MIXING INSTRUCTIONS:

Stir thoroughly before using.

### THINNING:

This product is supplied ready to use and need not be thinned. If thinning is required, clean water should be used, up to 20% by volume.

## APPLICATION:

We recommend the use of airless spray equipment. Roller or brushes can be also be used if spray equipment not available, but will not achieve a good level of finish due to the specific formulation of the product

**Do not** apply when the air or surface temperature is below 5°C or less than 3°C above dew point, or if this is likely to occur during the curing period.

**Do not** apply when there is rain, mist, fog, or snow imminent; when humidity is high or the surface is wet with condensation or likely to be during the drying period.

## CURING:

Touch dry:	10 minutes @ 15°C
Walk on time:	20 minutes @ 15°C
Traffic time:	40 minutes @ 15°C
Full cure:	2 Hours @ 15°C
Recoat:	1-2 hours @ 15°C

## TECHNICAL:

### COVERAGE:

Approx. 2.0m<sup>2</sup> per kg. This equates to 20 linear metres per kg

### FILM THICKNESS:

WFT thickness: 400 microns

## AFTERCARE AND MAINTAINENCE:

Uncured VersaLine can be cleaned off equipment and tools using clean water.

Laid product will tend to 'refresh' by action of rainfall and traffic. This can be accelerated if required, by use of brush and clean water or mild detergent. Floor coatings should not be scrubbed, or subjected to steam cleaning or hot water above 60°C.

## STORAGE:

### STORAGE CONDITIONS:

Storage area should be dry, protected from direct sunlight and extremes of temperature - i.e. between 5 and 20°C.

### SHELF LIFE:

6 months when stored under cover, in original unopened containers, in accordance with Storage Condition guidelines listed above.

### SIZES AVAILABLE:

Supplied in 20kg drums.

## HEALTH AND SAFETY:

Familiarise yourself with the material safety data sheets before using this product. If you need a copy please call our technical team on **023 9220 0606**.

### MEON UK

+44 (0)23 9220 0606  
MAIL@MEONUK.COM  
MEONUK.COM

### MEON IRELAND

+353 (0)1 840 7647  
INFO@MEONIRELAND.COM  
MEON.IE



**MEON**  
DELIVERING GREAT SURFACES