Technical Data Sheet

SAS Oil Tolerant Threadlock Revised 03.08.10

SAS Oil Tolerant Threadlock

PRODUCT DESCRIPTION

SAS243, SAS2430 is an anerobic formulation designed to be used on parts in an "as received" condition, such as those with protective films (oils) etc.

APPLICATIONS

SAS243, SAS2430 is designed for direct application onto as received parts where a light oily film exists or where contamination from surrounding parts is a problem.

INSTRUCTIONS FOR USE

- Where possible remove thick deposits of grease or dirt.
- Apply adhesive to threads and assemble parts.
- Parts should be left for 15 minutes to reach handling strength.
- Leave for 1 hour to fully cure.
- SAS243, SAS2430 (Standard/Fast) Activators can be used, however 30% strength loss can occur when using accelerators.

PROPERTIES

Use as a conventional medium strength locker on cleaned parts with strengths up to 12N/mm² or as a c onvenient all-purpose locker oroily parts with 8-10N/mm² typical strength depending on oil type and film.

TECHNICAL FEATURES

Resin	Mod Methacrylate
Colour	Blue Thixotropic
Cure speed	<15 mins @ 20°C
Viscosity – Brookfield Sp3 @20rpm @ 25°C	1200-1800 thixotropic
Gap fill	0.1mm
Flash Point	>85°C
Shelf life	12 months @ 20°C
Specific gravity	1.04
Max. Operating Temperature	-55°C to + 150°C

CURED PERFORMANCE

Full Cure Time	24 hours
Typical Breakaway Strength	19N/mm²
Typical Prevailing Strength	8-10N/mm ²

STORAGE

Store in a cool area out of direct sunlight. Shelf life > 12 months at ambient temperature.

HEALTH & SAFETY

This technical information sheet does not constitute a Material Safety Data Sheet (MSDS). Before using this product make sure you have read and fully understood SAS243, SAS2430 MSDS

PRESENTATION

Bottles	10ml, 25ml, 50ml, 250ml
Clam Packs	10ml, 25ml, 50ml