

**QUICK SPEC** 



## WARRANTY EXTENSION/RENEWAL - HYDROSTOP® PREMIUMCOAT® (HS-11)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project. Specifications are available at www.gaf.com.

Method	<ul> <li>Spray, roller, or brush apply HydroStop<sup>®</sup> PremiumCoat<sup>®</sup> Finish Coat</li> </ul>				
Requirements	<ul> <li>The existing HydroStop® Roofing System will be inspected to determine eligibility for recoat.</li> <li>Roof must be clean, dry, and tight.</li> <li>Adhesion test required to ensure proper adhesion to substrate(s).</li> <li>Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.</li> <li>GAF recommends that the surface temperature be at or less than 110°F (43°C) during application.</li> </ul>				
Application	1. Roof must be inspected before work begins. Any issues found during the inspection must be repaired prior to the application of additional HydroStop®				

## Instructions

- inspection must be repaired prior to the application of additional HydroStop PremiumCoat<sup>®</sup> Finish Coat.
- 2. Power wash roof to ensure it is free of dirt, debris, oil, and other contaminants that could negatively affect adhesion. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow to completely dry.
- 3. Apply HydroStop<sup>®</sup> PremiumCoat<sup>®</sup> System per the chart below.

SEAMS & DETAILS   HYDROSTOP® PREMIUMCOAT® SYSTEM							
Treatment Type	Product	Total (Gal/Sq)	DFT* (mils)				
3-Coursed Rates	HydroStop <sup>®</sup> Butter Grade and Fabric	4.0	43				
Flashing Grade Only Rates	HydroStop <sup>®</sup> Butter Grade	2.0	19				

WARRANTY EXTENSION/RENEWAL HYDROSTOP® PREMIUMCOAT® SYSTEM									
		Finish	Warranty						
	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Emerald Pledge™	Diamond Pledge™			
10 Year	0.75	0.75	1.50	13	Yes	Yes			
15 Year	1.00	1.00	2.00	17	Yes	Yes			

\* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor.

Note: DFT for 3-coursed rates includes 6 mils for the fabric.