



Test Report No. 70.405.16.53035.01

Dated 2017-01-04

ORIGINAL

Applicant: Henan Joinkona Medical Products Stock Co., Ltd
Xinxing Road, The South Of Industry District, Lushan County, Pingdingshan,
Henan Province, China
Attn: Ms. Cheng


Order No.: -
Style No.: -
Season: -
Manufacturer: Henan Joinkona Medical Products Stock Co., Ltd
Buyer: -
Country of Origin: -
Goods Export to: -

Care Label Provided: Do not wash, do not dry clean.

Receipt Date of Sample: Received on 2016-12-27
Date of Testing: From 2016-12-27 to 2017-01-04

Sample submitted: The sample(s) was (were) submitted by applicant and identified.

Test Result: Refer to next page.



TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai Branch

Testing Center

Prepared by:

Jessy Yang

Authorized by:

Elyn Yao

Jessy Yang
Softlines Department

Elyn Yao
Softlines Department

Note: (1)The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.

For full version, please visit: <http://www.tuv-sud.cn/cn-scn/terms-and-conditions>

(2)The results relate only to the items tested,(3)The test report shall not be reproduced except in full without the written approval of the laboratory

Laboratory:
TÜV SÜD Certification and Testing (China) Co.,
Ltd. Shanghai Branch Testing Center
Softlines Lab

Phone: +86 21 6037 6300
Fax: +86 21 6037 6350
E-mail: softlines@tuv-sud.cn
www.tuv-sud.cn/softlines

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai
Branch Testing Center Softlines Lab
2F Building B, No. 1999 Du Hui Rd, Minhang District,
Shanghai 201108 P.R. China




Test Report No. 70.405.16.53035.01

Dated 2017-01-04

ORIGINAL

Description of the test subject:

Sample	Description	Photo
001	SMS surgical gown in blue (XS/S/M/L/XL/XXL/XXXL)	

Conclusion:

Test Items		001
1	Flammability	Pass

Remark: Pass = Meet Client's Requirement
Fail = Below Client's Requirement
* = No Specified Requirement



Laboratory:
TÜV SÜD Certification and Testing (China) Co.,
Ltd. Shanghai Branch Testing Center
Softlines Lab

Phone: +86 21 6037 6300
Fax: +86 21 6037 6350
E-mail: softlines@tuv-sud.cn
www.tuv-sud.cn/softlines

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai
Branch Testing Center Softlines Lab
2F Building B, No. 1999 Du Hui Rd, Minhang District,
Shanghai 201108 P.R. China



Test Report No. 70.405.16.53035.01

Dated 2017-01-04

ORIGINAL

Test Results

- 1 **Flammability Test**
US CPSC16 CFR Part 1610
Fabric Surface: Smooth
Preliminary Testing: Lengthwise

(001)-base fabric	Flame spread(sec.)	Original state	Burn Code
(1)	-		IBE
(2)	-		IBE
(3)	-		IBE
(4)	-		IBE
(5)	-		IBE

Flammability Classification: Class 1

(001)-piping	Flame spread(sec.)	Original state	Burn Code
(1)	5.0		-
(2)	5.2		-
(3)	4.5		-
(4)	4.7		-
(5)	4.9		-
Average	4.9		-

Flammability Classification: Class 1

Washing procedure: According to § 1610.6(b)(1)(i)&(ii)

Remark: Class 1 - Normal Flammability
Textiles meeting these requirements are generally accepted by the trade as having no unusual burning characteristics.
Class 2 - Intermediate Flammability
Textiles meeting these requirements are recognized by the trade as having flammability characteristics between normal and rapid and intense burning.
Class 3 - Rapid and intense Burning
Such textiles are considered dangerously flammable and recognized by the trade as being unsuitable for clothing because of their rapid and intense burning.
IBE=Ignited but extinguished
*IBE=Ignited but extinguished, denotes a burn that goes under the cord without breaking the cord
DNI=Did not ignite
BB = Base burns.
SFuc = Surface flash under the code but does not break the cord.
SFpw = Surface flash, part way
SFpoi = Surface flash at point of impingement only.
SFonly = Time in second, surface flash only.
SFBB = Time in seconds, surface flash base burn.
SFBBpoi = Time in seconds, surface flash base burn starting at the point of impingement.

-End of Test Report-