



Hall's
MANUFACTURING

SUPERSHINE

TECHNICAL DATA SHEET



SUPERSHINE

Description

SUPERSHINE is a wax free, non-slip, polymer-based floor dressing specially designed to be antistatic and durable under heavy traffic conditions. It is easy to apply and extremely economical. Exhibits an immediate shine, without rubbing or buffing, with increased degrees of gloss after each application.

Technical data

Appearance: White Liquid Liquid
Odor Polymer
Viscosity 100 mPa.s at 25°C
Relative density 20°C 1,01 kg/l
pH 100% 20°C 7.5-8.5
Drying time 5-20min
Solubility in water 20°C complete

Instructions for use

Clean area/s to be dressed thoroughly ensuring that all polymers, waxes, acrylics and soils are sufficiently removed by using an approved polymer-stripping product.

After ensuring that the cleaned area/s are totally dry, apply by means of a mop, brush or roller and leave to dry.

Initially apply 3 to 4 coats always ensuring that the previous coat has dried before applying the next coat.

Wash with an approved light detergent every four weeks and apply one coat of SUPERSHINE if deemed necessary.

Whilst using this product ensure that the lid on the container is securely closed and tightened after each removal of liquid. This is to ensure that the product does not harden when not in use.

Storage stability

Store containers to prevent it from Leaking, store the container in a cool dry place.

Safety

R38: Irritating to skin.

R41: Risk of serious damage to eyes.

S25: Avoid contact with eyes.

S26: In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

ADVANTAGES

Non-toxic under normal conditions of use

Wax and resin free

Bio-degradable

Non-flammable

Anti-static

Economical

Non-slip

DISCLAIMER: All information given in this data sheet and by the company's technical staff is compiled from the information currently available to the company. The company accepts no responsibility whatsoever for its accuracy, or for any results which may be obtained by customers. Any customer who relies upon any advice or information given in this data sheet by the company or by its technical staff does so entirely at its own risk, and the company will not be liable for any loss or damage thereby suffered notwithstanding any want of care on the part of the company or its staff in compiling or giving the advice or information.

ISSUE DATE: January 2014