

### TECHNICAL DATA SHEET

Version 1 – 2015 SEPTEMBER THIS ISSUE SUPERSEDES ALL PREVIOUS PUBLICATIONS

## PRODUCT DESCRIPTION

Timbavarnish water based for ultimate protection for interior and exterior wood surfaces.

### PRODUCT USES

- Interior and exterior wood finish where a durable coating with a glossy finish is required.
- Ideal beams, skirting boards, window frames, furniture, fascia boards, fences, trellis, garden furniture, garage doors, shutters. Not suitable for Wooden Decks or Wooden Floors.

## **FEATURES AND BENEFITS**

- Has superior flexibility compared to conventional varnishes resists cracking and peeling.
- Attractive gloss finish enhances the natural beauty of wood.
- Nourishes and protects against harmful UV rays.
- Quick drying recoat in 4 hours.
- Solvent free water clean-up.

### PRODUCT INFORMATION

Appearance	Gloss
Colour	Clear only Users should become familiar with the colour by practising on well prepared scrap timber of the same type as is to be treated.as is to be treated.
Binder Type	Pure Acrylic
Density at 23°C	Approx. 1.04
Solids Content	By weight: Approx. 25% By volume: Approx. 22%
Packaged Viscosity	Viscosity at 23°C: Approx. 0.9 Poise
Spreading Rate	Approx. 10m <sup>2</sup> - 12m <sup>2</sup> per litre per coat depending on surface porosity, profile and application method.

Recommended DFT per coat Min. 25μm. Max. 35μm. Recommended WFT per coat Min. 55μm. Max. 75μm

Flash Point Non-Flammable





### APPLICATION INFORMATION

Mixing Stir until homogeneous with a flat paddle.

Surface conditions Surface Temperature between 10 - 35°C. Relative Humidity

between 10 - 85 % OR 2°C above dew point minimum.

Application methods Brush and spray applications

Thinner Brush: Apply in an even thickness and finish in the direction

of the grain. Thin the first coat up to 10% with water to aid penetration on raw wood. Allow to dry for 4 hours and sand lightly with 320 grit sandpaper. Apply second and third coat

undiluted, sanding lightly between coats.

Conventional Spray: Thin up to 10% with water.

N.B. Thinning reduces volume solids; therefore more coats will be needed to produce the same colour, build, gloss and

durability as for a brush application.

Drying Time Touch dry 1 hour at 23°C.

Recoating Time 4 hours at 23°C (Drying times will be extended during cold,

wet or humid conditions.)

Cleaning of equipment After use, remove as much product as possible, and then

clean immediately with water.

Substrates Suitable for application to correctly prepared beams, skirting

boards, window frames, furniture, fascia boards, fences, trellis, garden furniture, garage doors, shutters, and other

interior and exterior wooden surfaces.

Precautions: Do not apply during cold (below 10°C) or wet weather or on

to wet or damp wood. Drying times will be affected by

weather conditions.

Do not apply directly to bare metal surfaces – stop nail holes with wood filler. Ensure all sides of the wood, including joints and end-grain, are coated to prevent moisture from entering.

N.B. Woodgard Timbavarnish Water Based is not

recommended for floors or decking.

Coats Required For new work, apply three coats. Apply two coats for general

maintenance of a surface previously varnished in good

condition.



#### SURFACE PREPARATION

Ensure that surfaces are sound and free from dust, oil, grease, dirt, and debris. Surfaces must be thoroughly dry - no more than 12% moisture content.

#### **NEW SURFACES**

- Sand down wood including the end grain to a smooth even surface finish using 100 -150 grit sandpaper, sanding in the direction of wood grain. Note: If nail holes or wood crevices need to be filled with wood filler, then fill and allow drying and sand to a smooth finish as part of the final sanding.
- Remove dust with a clean lint free cloth dampened with water. Ensure that surface is now smooth, free from dust, dirt, grease, oil and mortar splatter. Surfaces must be thoroughly dry, no more than 12% moisture content.

## PREVIOUSLY VARNISHED

- Sound varnish must be wiped down with mineral turpentine to remove any wax, oil or silicone. Lightly sand surface with 320 grit sandpaper. Remove dust. Wipe or rinse the surface with clean tap water.
- Varnish that is cracked and flaked must be stripped to bare wood either by sanding or
  by the use of a paint stripper. Sand any discoloured areas to fresh wood. Sand down
  wood including the end grain to a smooth even surface finish using 100 -150 grit
  sandpaper, sanding in the direction of wood grain. Note: If nail holes or wood crevices
  need to be filled with wood filler, then fill and allow drying and sand to a smooth finish as
  part of the final sanding.

# PREVIOUSLY COATED WITH A WOOD TREATMENT THAT CONTAIN OIL OR WAX

- It is not recommended to varnish wood previously coated with a treatment containing oil or wax.
- Strip completely using a paint stripper. Sand down until all traces of previous treatment and discoloured wood have been removed
- Always sand in the direction of the grain. Remove dust. Wipe surface with cloth dampened with lacquer thinners and allow drying.

## PREVIOUSLY PAINTED SURFACES

• Strip completely using a paint stripper. Sand down until all traces of previous treatment and discoloured wood have been removed. Always sand in the direction of the grain. Remove dust. Wipe surface with cloth dampened with mineral turpentine.





## **HEALTH AND SAFETY INFORMATION**

This product contains no added lead. Avoid contact with skin or eyes. Keep out of reach of children. If accidently swallowed, seek medical advice immediately and show this container to the doctor. Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes.

If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used. Do not empty into drains or watercourses.

Ensure good ventilation during application and drying. It is recommended to use suitable protective clothing and equipment. To avoid the risk of spillage, always store and transport containers in a secure upright position. Refer to Material Safety Data Sheet for complete information.

### ADDITIONAL INFORMATION

Packaging	1lt, 5Lt
i adhaging	110, 00

Storage Conditions Store under cool dry well-ventilated conditions, below 25°C,

away from direct sunlight, heat and extreme cold.

Disclaimers Colour swatch references are as accurate as modern

printing will allow. For best colour and sheen consistency, it is advisable to use containers from the same batch number. In the case of different batch containers it is recommended that they be mixed together in a large container before use.

Woodgard colours are translucent to allow the natural beauty of wood grain to show through, the original colour of

the wood will impact the final finishing colour.

The AkzoNobel Logo, the Flourish, the Dulux logo, the Woodgard logo, the Planet Possible logo, Dulux and Woodgard are all trademarks of the AkzoNobel group ©

AkzoNobel 2015.

## TDS STANDARD DISCLAIMER

The recommendations contained herein are given in good faith and meant to guide the specifier or user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Dulux control.

Important Note; Technology may change with time, necessitating changes to this Technical Data Sheet (TDS).

It is the responsibility of the user to ensure that the latest TDS is being used for reference. Dulux Technical Data Sheets are available on our website <a href="www.dulux.co.za">www.dulux.co.za</a> or please contact: Dulux On-Line on 0860 330 111. Email <a href="mailto:ZA.Helpline@akzonobel.com">ZA.Helpline@akzonobel.com</a>

ICI Dulux (Pty) Ltd is part of AkzoNobel. ICI Dulux (Pty) Ltd Reg No.1946/020769/07

