

## FINE LIME PLASTER

Smooth lime-based coating with mica particles for a beautiful mineral finish.



### RECOMMENDED USE

#### Indoors.

For vertical surfaces, in all dry rooms.

Substrates: All standard building materials that have been properly primed.

### BENEFITS

Contains mica particles for a beautiful effect. Does not chalk, allows materials to breathe.

### SURFACE PREPARATION

The surface must be perfectly cleaned, dusted and dry. Wash off any remaining old paint, then sand and dust again, if necessary. To prepare the substrate, only use the following products:

**On low-porosity surfaces:** Generously cover with our Rough Primer but avoid any build-up of thickness to ensure the plaster adheres to the surface.

**On porous or powdery substrates:** Apply a coat of Universal Primer to nourish the substrate, then a coat of Rough Primer.

**Application tools:** A trapezoidal plastering trowel or stainless steel smoothing trowel for the undercoat.

A stainless steel smoothing trowel for the Fine Lime Plaster.

A Mercury Ultra 37 Scraper to sand the Fine Lime Plaster.

### APPLICATION

Generously cover the surface with Rough Primer but avoid any build-up of thickness to ensure the plaster adheres to the surface.

**Undercoat for Mineral Plaster:** After the Rough Primer has dried (approx. 12h), apply the Undercoat for Mineral Plaster using the trapezoidal trowel and cover the surface in fine layers making rounded continuous movements. Start at the top of the wall and make your way down without exerting too much pressure. Adjust the thickness to the Rough Primer.

Work on surfaces of approx. 2 to 4m<sup>2</sup> and leave the walls to dry when your work is complete. Drying time: 12h.

**Fine Lime Plaster:** Gently stir the plaster until smooth. Using the the stainless steel smoothing trowel, cover the surface with fine layers making rounded crisscrossing movements ensuring even thickness all over. Adjust thickness to the undercoat. Work on small areas starting at the top of the wall.

When the Fine Lime starts to go matte, smooth with the stainless steel smoothing trowel in crisscrossing movements from right to left. Work on small surfaces [20 to 30cm<sup>2</sup>]. Drying time: 12h. Do not touch the plaster while it is drying to avoid fingerprints.

Once the plaster is dry, sand lightly using the Mercury Ultra 37 Scraper to reveal the shiny particles and remove any defects. Dust the surface carefully protecting your floor with a suitable plastic cover and vacuum if necessary.

This product contains slaked lime so it is essential you wear protective gear throughout the application process, as well as a mask while sanding and dusting.

**Protection (Optional step):** Leave the plaster to dry for 3-4 days. Fine Lime Plaster may be protected from water and grease splashes by using a Fixative for Lime Paint, a special protective coating.

Refer to the technical data sheet.

## APPLICATION

Wait 24h until the surface has dried completely to appreciate the final result and for an optimal water and oil repellent effect.

NB: The protective coating may intensify the shade.

## GENERAL INFORMATION

**Appearance:** Matte.

**Coverage:** Undercoat for Mineral Plaster: 1.3-1.6m<sup>2</sup>/kg.  
Fine Lime Plaster: 2.5-3 m<sup>2</sup>/L.

**Drying time:** Undercoat for Mineral Plaster: 30 mins dry to the touch.  
Fine Lime Plaster: Approx. 12h.

**Second coat:** Variable depending on temperature and air humidity.  
Undercoat for Mineral Plaster: 12h.  
Fine Lime Plaster: You can cover the Fine Lime Plaster with a protective coating intended with Fixative for Lime Paint, 3-4 days after application.  
Please read our instruction sheet Number 966 carefully.

**Solid content:** Undercoat for Mineral Plaster: 76% in weight, 55% in volume.  
Fine Lime Plaster: 69% in weight, 46% in volume.

**Density:** Undercoat for Mineral Plaster: 1.9g/cm<sup>3</sup>.  
Fine Lime Plaster: 1.6g/cm<sup>3</sup>.

**How to clean your equipment:** Water.

**Packaging:** Undercoat for Mineral Plaster: 5kg and 20kg.  
Fine Lime Plaster: 3L and 12L.

**Storage:** 1 year in its original unopened packaging. Keep away from frost.

## HANDLE WITH CARE

Use in temperatures between +5°C and + 30°C. Do not use when relative humidity reaches more than 75%. This plaster contains slaked lime so it is essential you protect your eyes and wear gloves while applying.

## REGULATORY INFORMATION

**AFNOR Classification:** Family III - Class 2.

**VOC<sup>(1)</sup>:** Undercoat for Mineral Plaster: The 2010 EU limit value for this product (cat A/I) is 200g/L. This product contains maximum 2g/L VOC.  
Fine Lime Plaster: The EU limit value for this product (cat A/I) is 200g/L. This product contains maximum 20g/L VOC.

**Safety:** Refer to the Safety Data Sheet (SDS). Complies with current legislation.

<sup>(1)</sup> Volatile Organic Compounds: Directive 2004/42/EC.

\* Information on the emission of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on the class scale from A+ (very low emissions) to C (high emissions).