



Capliner

Product Specification Sheet

TEST METHOD	PROPERTY	SPECIFICATION
N/A	Construction	100% Polyester ecofi® Nonwoven Material
FTM NW508 (ASTN D3776)	Weight	281.42gsm +/- 27.12gsm
FTM NW502 (ASTM D3774)	Width	2.15m
FTM NW504 (ASTM D1777)	Thickness	3.55mm +/- 0.38mm
FTM NW505 (ASTM D5034)	Tensile Strength	MD 52kg min CMD 63kg min
FTM NW506 (ASTM D5034)	Elongation INSTRON @ pre-set point (11kg)	MD 55% +/- 15% CMD 50% +/- 15%
Visual	Colour	Platinum, Shadow
Visual	Appearance	Match Approved Standard



BluSky Products Pty Ltd ABN 71 616 950 371

A: 28 Sunblest Crescent Mount Druitt NSW 2770 Australia

P: +61 2 98320848 F: +61 2 98320843 E: info@bluskyproducts.com.au

www.bluskyproducts.com.au