

METALLIKA



TECHNICAL DATA METALLIKA

Issued on 03/12/2013 - Rev. n. 1 of 05.09.2023

FEATURES AND USES

Metallic decorative finish, METALLIKA is used as a finish for floors and walls with a highly visible metallic effect.

Composition:

Special acrylic emulsion, unalterable metallised biostable pigments resistant to U.V., pigments and various additives.

Preparation of the base:

On well-consolidated substrates, perfectly smooth and painted with white or colored washable water-based paint, the application does not require any primer.

Applications:

Walls: apply a first layer of METALLIKA, using a spalter brush, making irregular movements, with crossed strokes, on the surface; after drying, after about 12 hours, repeat the operation as already done for the first layer, to obtain the desired brushed effect and optimal coverage.

Floors: apply a first layer of METALLIKA using a stainless-steel trowel, repeat the operation as already done for the first layer, to obtain the desired brushed effect and optimal coverage.

TECHNICAL DATA:

SPECIFIC WEIGHT: 1,080 +/- 5% Kg./Lt.

COLOR: colourable colors in our color tinting system 3.0 tinting system

VISCOSITY: BROOKFIELD: 4300 cps ± 5% G6 RPM 100 at 25 ° C

YIELD: 20 m²/Lt. Depending on the absorption of the product

DILUTION: ready to use

PACKAGING: polyethylene containers of Lt. 2.5 - Lt. 1

DRYING: to the touch 1 h, in depth 24h to 20 ° C

TEMPERATURE LIMIT OF USE: + 5 ° C / + 35 ° C

APPLICATION: brush, spalter

STORAGE: in original sealed packaging and in a dry place between + 5 ° C and + 30 ° C.

RESISTANCE TO WASHING: resistant to washing > 5000 Gardner cycles UNI 10795 UNI 10560

PERMEABILITY TO WATER STEAM: high UNI 10795 UNI EN ISO 7783-2

RESISTANCE TO ALCALS: resistant to alkali UNI 10795

DIRT TANK: low UNI EN 10792

Conforming to the UNI EN 15457 standard (resistance to the growth of fungi), due to the presence of specific additives with a broad spectrum of action, it allows the product to prevent the formation of mold, fungi, algae, and moss over time. All the technical information contained herein is indicative. These values have

Nikkolor Italia s.r.l.

V.le Vittorio Veneto, 186 - 96014 Floridia (SR)

+39 0931 941789 - www.nikkolor.net



been obtained in our laboratories in a conditioned environment and can undergo changes due to the different conditions of installation.

The use of coloring pastes not supplied by Nikkolor Italia can compromise not only the aesthetic appearance but above all can significantly alter the performance of the product itself.

The data contained in these technical sheets refer to laboratory tests. The indicated indications and methods may be subject to changes over time according to possible improvements in production technologies. The application of the products takes place beyond our control as we cannot directly intervene on the conditions of the construction sites and on the execution of the works. All indications are of a general nature, they do not bind our company in any way and therefore the responsibility falls exclusively on the customer. A preventive test of the product is recommended in order to verify its suitability for the intended use. Our technical service is available to provide additional information.