

Technical Data Sheet n° C 506.20

page 1 of 2 Ver. 1.2/0520

CASEINA

Water-based one component transparent natural topcoat for CALCETERRA

Product characteristics and uses

CASEINA is a one component natural water-based transparent protective topcoat that enhances the colour and appearance of surfaces made with CALCETERRA. The product can also be coloured with NATURAL SANDS to create glazing or distressed effects.

Surface preparation

After CALCETERRA has been applied and the walls are completely dry, CASEINA may be applied.

Product preparation

CASEINA must be stirred before use.

- Hardening: one component product
- Dilution: AS A TOPCOAT: about 30% with water
 AS GLAZING: about 30 40% with water

Application method

CASEINA is applied as one or more coats by sponge, brush or roller. For colouring and glazing, apply wet on wet to overlay several combinations of CASEINA and NATURAL SANDS. The surface can also be reworked with a clean damp sponge to soften the colours and create distressed effects.

Colours

CASEINA is a matt transparent topcoat (about 0 Gloss) which can also be coloured by NATURAL SANDS. The amount of NATURAL SANDS and water that has to be added to CASEINA changes according to the desired colour intensity.

Application and storage conditions

- Application temperature: between +15°C and +35°C
- Storage temperature: between +5°C and +35°C
- Cleaning tools: use warm water



Technical Data Sheet n° C 506.20

page 2 of 2 Ver. 1.2/0520

Technical Features

TECHNICAL DATA	UNIT of MEASUREMENT	VALUE
VOC	g/L	1.37 g/L (maximum)
Dilution	-	About 30% with water (TRANSPARENT) From 30-40% with water (GLAZING)
Approximate coverage	Kg/sqm	0.1 - 0.13 Kg/sqm (two coats)

Reaction Times (e.g. temperature 20°C and 50% relative humidity)

Dust dry time: about 30-45 minutes
 Touch dry time: about 1-2 hours
 Recoating time: about 1-2 hours
 Complete drying: about 4-6 hours

Packaging

• 1L

4 L

CERTIFICATION:



For further information contact the technical office Gruppo GANI at the number +39.031.905163.

The information contained in this technical card are based on the common experience in the sector, without specific implicit or explicit guarantee. The application and the use of our products take place outside our control possibilities and so those fall down under the exclusive responsibility of the user.