

26 October, 2005



Astec Paints Australasia Pty Ltd
262 Marion Road
NETLEY SA 5037

Attention: Mr Mark Waters

REPORT 05MAAD09735 – Part 3

CLIENT REFERENCE: Request

TITLE: Astec BASIX test

SAMPLE IDENTIFICATION: Astec Energy Star Tilesshield

WORK REQUESTED: Determine colour classification according to Basix Thermal Comfort Protocol.

INVESTIGATING OFFICER(S): Natalie Powell

Monty Luke
Laboratory Manager
Materials Services

Amdel Limited shall not be liable for loss, cost, damages or expenses incurred by the client, or any other person or company, resulting from the use of any information or interpretation given in this report. In no case shall Amdel Limited be liable for consequential damages including, but not limited to, lost profits, damages for failure to meet deadlines and lost production arising from this report. This document shall not be reproduced except in full and relates only to the items tested. Samples will be stored for thirty days. Ref: g:\building\natalie\05 maad jobs\clients a- e\astec paints 05maad09735\05maad09735 astec paints pty ltd part 3 logo.doc Page 1 of 4

1. INTRODUCTION

Mark Waters of Astec Paints Pty Ltd supplied reflectance and emittance data of Astec Energy Star Tilesheet samples of various colours to the Amdel Materials Services Laboratory. It was requested that Amdel should carry out calculations to determine the colour classification according to the BASIX Thermal Comfort Protocol. The samples supplied for evaluation were identified as follows.

- ❖ Astec Energy Star Tilesheet
- ❖ Astec Energy Star colours

2. PROCEDURE

The sample data supplied were inserted into the American Cool Roof Rating Council ASTM E 1980-01 calculator. Standard solar conditions of Solar Flux = 1000W/m² Ambient Air Temp = 310K (37°C), Ambient Sky Temp = 300K (27°C) and no conductive heat transfer were used for all calculations. Each sample used the Emittance value for Astec Energy Star Tilesheet white base of 0.90.

3. RESULTS

- ❖ Colour Classifications

The results of the calculations of the Astec Energy Star Tilesheet sample were as follows.

<u>Colour</u>	<u>Solar Absorbance</u>	<u>BASIX Classification</u>
White Base	0.106	Light
8068 C/B Heritage Red	0.625	Medium
8069 Red Iron Oxide	0.610	Medium
8070 Terracotta	0.576	Medium
8071 Clay Tone	0.533	Medium
8072 Warm Clay	0.405	Light
8073 Tuscany	0.340	Light
8074 C/B Ironbark	0.594	Medium
8075 Pioneer	0.712	Dark
8076 Regal Brown	0.614	Medium
8077 Yallara Brown	0.630	Medium
9078 C/B Weathered Copper	0.609	Medium
8079 Charcoal	0.672	Medium

<u>Colour</u>	<u>Solar Absorbance</u>	<u>BASIX Classification</u>
8080 C/B Slate Grey	0.597	Medium
8082 Nimbus	0.645	Medium
8083 C/B Beige	0.457	Light
8084 Merino	0.317	Light
8085 Off White	0.253	Light
8086 Sandalwood	0.233	Light
8087 C/B Smooth Cream	0.215	Light
8088 Mocca	0.424	Light
8089 Stone	0.311	Light
8098 Carraige Green	0.754	Dark
8099 Bruns Green	0.741	Dark
8100 Mist Green	0.560	Medium
8101 C/B Rivergum	0.555	Medium
8102 Olive Green	0.606	Medium
8103 Blue Grass	0.640	Medium
8104 Botanic	0.721	Dark
8105 French Green	0.461	Light
8108 C/B Mountain Blue	0.745	Dark
8081 C/B Birch Grey	0.378	Light
8094 Quarry	0.402	Light
8095 Mid Biscuit	0.305	Light
8097 Light Latte	0.291	Light
8106 C/B Saltbush	0.442	Light
8107 Cobalt	0.662	Medium
8110 Pewter	0.393	Light
8111 Autumn	0.391	Light
8112 Chino	0.394	Light
8091 Broken White	0.187	Light
8092 Neutral White	0.215	Light

<u>Colour</u>	<u>Solar Absorbance</u>	<u>BASIX Classification</u>
8093 Pale Biscuit	0.246	Light
8096 Light Cream	0.213	Light
809 Gull Grey	0.317	Light