


Glass Fiber Reinforced PP

Technical Datasheet




Glass Fiber Reinforced PP

FL500PP-GF

Xtellar glass fiber PP filaments are an engineering-grade composite made with glass fiber (GF) and is designed to provide robust impact strength performance while maintaining a high degree of printability for complex structures. This fiber reinforced pellet provides engineering level performance without compromising any of PP's inherent properties which include light weight, water resistance (no drying needed), chemical resistance, and impact resistance.

Printing Conditions

Nozzle Temperature	240°C / 464°F
Bed Temperature	85°C / 185°F
Printing Speed	30-55 mm/s
Fan Speed	50%
Nozzle Type	Hardened
Bed Material	Glass
Bed Adhesion Method	Magigoo PP or PPGF



Material Properties

Property	Standard	Bulk	Print Orientation	
			XY	XZ
Density @ 23°C, g/cm ³	ASTM D792	1.05	1.06 ± 0.00	
Melt Flow Rate @ 230°C / 2.16 kg, g/10min	ASTM D1238			
Hardness, Shore A	ASTM D2240		95 ± 0.8	
Hardness, Shore D	ASTM D2240		58 ± 3.7	
24 h Water Absorption, wt%	ASTM D570			

1735 Market St #28
Philadelphia, PA 19103
Phone:
Email:


xtellar

Version 1.1
Revision Date: April 29, 2023

DISCLAIMER: The values and information provided in this document are representative of typical values and should not be considered for design specifications or quality control purposes. The information contained in this document does not constitute a guarantee or warranty of any kind, either express or implied, regarding the performance or use of the product. Xtellar does not make any warranties, express or implied, regarding the suitability or fitness of its products for any specific purpose. It is the customer's responsibility to determine whether the product is safe, legal, and technically appropriate for the intended use. The information provided herein is not a license to operate or a recommendation to violate any patents.

Glass Fiber Reinforced PP

Technical Datasheet



Properties are measured in Bulk (injection molded), XY and XZ orientations. Samples were printed using processing conditions comparable to those in the Printing Conditions table on Page 1.

Thermal Properties

Property	Standard	Bulk	Print Orientation	
			XY	XZ
Glass Transition Temperature (T _g), °C	ASTM E1640	-57.7 ± 0.4		
Melting Temperature (T _m), °C	ASTM D3418	166		
HDT @ 0.45 MPa, °C	ASTM D648		144.7 ± 2.3	79.3 ± 6.4
HDT @ 1.82 MPa, °C	ASTM D648			
Vicat Softening Temperature @ 10 N, °C	ASTM D1525		152.1 ± 0.5	150.5 ± 0.7
Mean CTE @ -50°C to 100°C, μm/m•k	ASTM E831			

Flammability

Property	Standard	Bulk	Print Orientation	
			XY	XZ
Onset of Resin Degradation, °C	ASTM D2584		348	
Linear Rate of Burning (100 mm), mm/min	ASTM D635			
25 mm Burn Time, s	ASTM D635			
Afterflame Time, s	ASTM D3801			
Afterglow Time, s	ASTM D3801			
Contact Ignition	ASTM D3801			

Electrical

Property	Standard	Bulk	Print Orientation	
			XY	XZ
Surface Resistivity, Ohm (Ω)	ASTM D257			
Volume Resistivity, Ohm-m (Ω-m)	ASTM D257			
Surface Conductivity, mS/m	ASTM D257			
Volume Conductivity, mS/m	ASTM D257			

1735 Market St #28
Philadelphia, PA 19103
Phone:
Email:


xtellar 

Version 1.1
Revision Date: April 29, 2023

DISCLAIMER: The values and information provided in this document are representative of typical values and should not be considered for design specifications or quality control purposes. The information contained in this document does not constitute a guarantee or warranty of any kind, either express or implied, regarding the performance or use of the product. Xtellar does not make any warranties, express or implied, regarding the suitability or fitness of its products for any specific purpose. It is the customer's responsibility to determine whether the product is safe, legal, and technically appropriate for the intended use. The information provided herein is not a license to operate or a recommendation to violate any patents.

Glass Fiber Reinforced PP

Technical Datasheet



Properties are measured in Bulk (injection molded), XY and XZ orientations. Samples were printed using processing conditions comparable to those in the Printing Conditions table on Page 1.

Mechanical Properties

		Property	Standard	Print Orientation	
				XY	XZ
Tensile		Tensile Strength @ Yield, MPa		43.6 ± 1.5	8.9 ± 0.7
		Tensile Strength @ Break, MPa		43.1 ± 1.0	8.9 ± 0.7
		Tensile Elongation @ Yield, %	ASTM D638	2.3 ± 0.5	1.6 ± 0.5
		Tensile Elongation @ Break, %		2.5 ± 0.5	1.7 ± 0.6
		Tensile (Young's) Modulus, MPa		5,035 ± 141	1,100 ± 49
Flexural		Flexural Strength @ 1% Strain, MPa		35.2 ± 0.4	5.6 ± 0.7
		Flexural Strength @ Break, MPa		(NB)	(NB)
		Flexural Strain @ Break, %	ASTM D790	(NB)	(NB)
		Flexural Modulus @ 1% Strain, MPa		3518 ± 37	560 ± 65
		Flexural Modulus @ Break, MPa		(NB)	(NB)
Compression		Compressive Strength @ Yield, MPa		43.2 ± 0.9	36.1 ± 1.6
		Compressive Disp. @ Max Load, %	ASTM D695	8.4 ± 0.6	8.4 ± 0.6
		Compressive Modulus, MPa		1,123 ± 41	427 ± 30
Unnotched Izod		Impact Strength @ 23°C, J/m		392.8 ± 48.8 (P)	79.7 ± 7.3 (C)
		Impact Strength @ 0°C, J/m	ASTM D4812	397.4 ± 21.3 (C)	42.5 ± 35.1 (C)
		Impact Strength @ -20°C, J/m		376.6 ± 35.7 (C)	4.6 ± 1.2 (C)
Notched Izod		Impact Strength @ 23°C, J/m		179.2 ± 5.1 (P)	31.8 ± 4.0 (H)
		Impact Strength @ 0°C, J/m	ASTM D256	131.2 ± 3.5 (P)	15.5 ± 1.7 (C/H)
		Impact Strength @ -20°C, J/m		105.6 ± 6.2 (P)	7.1 ± 3.6 (C)
Charpy Impact		Impact Strength @ 23°C, kJ/m ²		21.8 ± 0.8 (H)	4.2 ± 0.3 (C)
		Impact Strength @ 0°C, kJ/m ²	ISO 179	16.2 ± 0.8 (P)	2.7 ± 0.4 (C)
		Impact Strength @ -20°C, kJ/m ²		13.6 ± 0.5 (H)	2.1 ± 0.3 (C)

¹ Parenthesis denote break type (C) = Complete, (P) = Partial, (H) = Hinge, (NB) = No Break

1735 Market St #28
Philadelphia, PA 19103
Phone:
Email:



Version 1.1
Revision Date: April 29, 2023

DISCLAIMER: The values and information provided in this document are representative of typical values and should not be considered for design specifications or quality control purposes. The information contained in this document does not constitute a guarantee or warranty of any kind, either express or implied, regarding the performance or use of the product. Xtellar does not make any warranties, express or implied, regarding the suitability or fitness of its products for any specific purpose. It is the customer's responsibility to determine whether the product is safe, legal, and technically appropriate for the intended use. The information provided herein is not a license to operate or a recommendation to violate any patents.