

EVERFLEX AC95 ACOUSTIC SEALANT AND ADHESIVE

Colour	Product Code	Pack Size	Box Qty
White	AC95900	900ml	9

Product Description

AC95 is a high strength, permanently flexible acoustic/intumescent sealant and adhesive specifically formulated for sealing and bonding plasterboard and other Kraft lined insulation boards, where a fire rated seal of up to 5 hours is required. Water based, solvent free formula, easy to use and clean up and adheres to just about all building substrates. Non-flammable.

Conforms EN1366-4: 2006, Independently tested by Warrington Fire Research, Report Number 181967 (May 2009). Acoustic rated to BS EN ISO 140/3. Tested for air permeability to EN13141-1 Ventilation for buildings. Performance testing of components/products for residential ventilation.

Benefits

- Forms a fire rated acoustic barrier – up to 5 hour fire rating – 25% greater than conventional/competitive fire rated sealants.
- Permanently flexible/high grab
- Adheres to most surfaces.
- Mould resistant.
- Non flammable
- Overpaintable.
- Easy clean up

Areas For Use

- To form an acoustic and intumescent barrier by sealing gaps between plasterboard walls, floors and ceilings and dry lining applications.
- As an adhesive to bond plasterboard to plasterboard and to bond plasterboard to wood and metal studding and direct to block work.
- For sealing and bonding most other kraft lined insulation boards.

Limitations

- Damp or humid conditions will significantly extend the cure time.
- Do not attempt to abrade when cured.
- Do not overpaint until product has fully cured. This will normally be 24 hours but may be 4-5 days in damp, cold or humid conditions.
- Do not apply below 5°C.
- For overhead boarding applications, always use in conjunction with mechanical fixings.

Surface Preparation

All surfaces must be clean and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application. Highly porous substrates such as new plaster should first be primed with Everbuild PVA bond diluted 1:4 with water. Surfaces may be slightly damp, but not wet. NOTE: THIS WILL SLOW THE CURE.

Application

Fit cartridge into a 1ltr mastic gun. Cut nozzle to required length and puncture inner membrane seal before applying.

Use as a sealant: Always cut nozzle to a size slightly larger than the gap to be sealed.. Apply to gap, slightly overfilling and finish smooth with a caulking tool or filler knife. Clean up any excess with a damp cloth within 30 minutes of application.

Use as an adhesive for direct bonding to large surfaces: Cut nozzle to provide a bead of approximately 9-10mm diameter, pierce inner membrane and apply a continuous bead to one surface at 250-350mm centers. Apply board immediately to surface and tamp down. Provide temporary support until cured.

Use as an adhesive for bonding to studding: Apply a continuous bead to studding and apply board immediately into position. Do not apply more than one board's width of studding at one time. Provide temporary support until cured.

Specific Data

Form	Ready to use thixotropic paste	
Specific Gravity	1.57-1.60	
Elongation at Break (%)	100-200%	
Hardness (Shore A)	Approximately 40	
Tack Free Time	15 to 60 mins, dependent on thickness, ambient temperature and humidity	
Full Cure	1 to 5 days, dependent on thickness, ambient temperature and humidity	
Solids Content	83%	
Slump Resistance	No slump at 25°C when placed in a 20mm x 10mm vertical channel	
Application Temp. Range	+5°C to +40°C	
Service Temp. Range	-15°C to +70°C	
Chemical Resistance	Dilute Acids - Fair	Dilute Alkaline - Fair
	Aliphatic Hydrocarbons - Fair	AromaticHydrocarbons - Poor
Movement Accommodation	Low to medium (+/- 7.5%)	
Durability	Up to 15 years when used as recommended	
Compatibility	Can be used in contact with most building and decorating materials but Should not be used against bituminous materials.	

FIRE TEST RESULTS – WALL SPECIMENS

SPECEMIN	GAP FACE MATERIAL COMBINATION	WIDTH/DEPTH MM	BACKING MATERIAL	INTEGRITY (MINS)	INSULATION (MINS)
G	Aerated concrete/Aerated concrete	12/6	PE open cell foam	301	222
H	Aerated concrete/aerated concrete	30/15	PE open cell foam	301	301
I	Aerated concrete/softwood	12/6	PE open cell foam	108	75
J	Aerated concrete/hardwood	12/6	PE open cell foam	153	152

FLOOR SPECIMENS

SPECEMIN	GAP FACE MATERIAL COMBINATION	WIDTH/DEPTH MM	BACKING MATERIAL	INTEGRITY (MINS)	INSULATION (MINS)
A	Aerated concrete/aerated concrete	12/6	PE open cell foam	301	196
B	Aerated concrete/aerated concrete	30/15	PE open cell foam	301	81
C	Aerated concrete/aerated concrete	50/25	PE open cell foam	301	74
D	Aerated concrete/Steel	12/6	PE open cell foam	301	43

Full set of specimen results detailed in test report 181967, available on request. The overall test was discontinued after a period of 300 mins.

Health & Safety

Consult MSDS for full list of hazards

Storage

Store in cool dry conditions and protect from frost.

Shelf Life

12 months from date of manufacture.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.