



LOW-FIRE CLAY	SKU	$\Delta 04$ Shrinkage	$\Delta 1$ Shrinkage
LF06 White	13500B	9.0%	11.0%
Pipenberg Raku	13527B	7.5%	10.0%
Raku II	13526B	8.5%	9.0%
Redart Terracotta	13530B	8.0%	13.5%
Redart Terracotta w/ Sand	13531B	6.0%	12.0%
Wolf Creek White	13570B	7.5%	10.0%

MID-RANGE CLAY	SKU	$\Delta 5$ Shrinkage
Alpine White	12655B	11.68%
Awaji Porcelain	12690B	11.39%
CKK6	12651B	11.66%
CKK6 w/ Grog	12653B	9.64%
Dove Porcelain	12660B	13.77%
Eclipse Pottery Clay	12698B	10.13%
Fool's Gold Pottery Clay	12696B	13.9%
Klamath Brown	12634B	11.37%
Klamath Buff	12633B	10.88%
Klamath Red	12631B	11.73%
Klamath White	12632B	11.48%
Klamath Yellow	12635B	12.0%
Sea Mix 6	12648B	11.32%
Sea Mix 6 w/ Grog	12657B	11.08%
Sea Mix 6 w/ Sand	12654B	10.29%
Sea Mix Speckled	12649B	11.09%
Seattle Freeze	12691B	10.67%
Vashon Buff	12609B	14.34%
Vashon Buff w/ Grog	12616B	11.45%
Vashon Gray	12613B	11.54%
Vashon White	12608B	13.25%
Vashon White w/ Grog	12607B	12.21%

# SEATTLE POTTERY SUPPLY

## SHRINKAGE CHART

HIGH-FIRE CLAY	SKU	$\Delta 10$ Shrinkage
Columbia Buff	11723B	12.5%
Columbia White	11750B	13.5%
Flameware	11825B	10.0%
Grolleg Porcelain	11840B	12.5%
Kenzan Porcelain	11850B	12.5%
Mt. Baker White	11775B	11.0%
Pine Lake White	11760B	14.0%
Sculpture Buff - Coarse	11770B	11.0%
Sculpture Buff II - Fine	11771B	11.0%
Sea Mix 10	11844B	12.5%
Sea Mix 10 w/ Grog	11846B	12.0%
Suzuki Porcelain	11805B	10.5%
TBT	11860B	12.5%

Clay shown is SPS Eclipse, as greenware, bisque-fired, and glazed. Fired at  $\Delta 5$ . Made by SPS team potter Denny Porter.

[www.seattlepotterysupply.com](http://www.seattlepotterysupply.com)