

广州新莱福磁材有限公司
Guang Zhou Newlife Magnetics Co.,Ltd.

产品仕様书

SUPPLY SPECIFICATION SHEET

客户名称:

Customer:

品名: 防锈铁粉片

Part Name: ANTI-RUST IRON SHEET

型号:

Drawing No.: ANTI-RUST IRON SHEET

日期:

Date: 2024/3/20

批准 Comfirmer	审核 Auditor	编制 Editor
汪晓阳	吴隆章	任治家
承认签署: APPROVED BY:		

Version: A0

NMEQS-1450

规格 (Size) :

1、ANTI-RUST IRON SHEET 30M×25×1.0mm/Matte white PVC/3M9448 adhesive

尺寸和公差 (Dimensions: & Tolerance) :

Item	Length (m)	Width (mm)	Thickness (mm)	Thickness of adhesive(mm)	Thickness of pvc(mm)
Size	30	25	1.0	0.27	0.10
Tolerance	0/+0.6	±0.3	±0.1	±0.03	±0.01

吸力 (Pull Strength) :

使用直径 6mm, 表磁 3800Gs 钕铁硼颗粒测试吸力:1.0≥200g

holding force: 1.0≥200g

Testing condition: the test tool is NdFeB particle (diameter is 6mm, superficial magnetic field is 3800Gs)

物理参数 Physical Data:

Total thickness (mm) 总厚度	1.37±0.14
Reference Weight (g/m ²) 克重	3910±391
Hardness (Shore D) 硬度	40±5
Flexibility (Φ6mm 铁圆柱) 柔韧度	Without cracking
Opacity 不透明度	100%

产品保存 Storage:

工作条件：最佳温度范围是 21°C--38°C，建议若初始粘贴温度低于 10°C 的条件不用于粘接，因为此时胶粘剂太硬而无法牢固地粘贴在物体上。但是，如果已正确地粘贴上，低温下地持粘力同样达到理想状态。

Working Condition: The optimum temperature range is 21 °C--38°C. It's not recommended to apply while the initial temperature is lower than 10°C, because the adhesive is too hard to paste on the object completely. However, if it has been affixed properly, the sticking force of adhesive can keep in ideal state in the low temperature.

储存条件： 25°C 和 50%相对湿度

Storage Condition: 25° C and 50% humidity conditions

保质期:原包装状态下自生产之日起贮存期为 12 个月

Shelf life: 12 months under original packaging condition