

August 6, 2019

-TEST REPORT-

PN 149079

PHARMACEUTICAL SERVICES

Prepared For:

Jim Stock Tian's International, Inc. 600 S. Kraemer Blvd. Brea, CA 92821

Prepared By:

Tiffany Heller Manager, Pharmaceutical Services Approved By:

Ana C Barbur, M.S.

Vice President, Analytical & Chemical Services

Rev 101218



An A2LA ISO 17025 Accredited Testing Laboratory — Certificate Numbers 255.01 & 255.02 ISO 9001:2015 Registered

ISO 9001:2015

Registered

Letters and reports are for the exclusive use of the clients to whom they are addressed and shall not be reproduced, except in full, without the written permission of Akron Rubber Development Laboratory, Inc. (ARDL). The information contained herein applies to the specific material, products or processes tested or evaluated. No warranty of any kind is herein construed or implied. The liability of ARDL, Inc. shall be limited to the amount of consideration paid for services. ARDL, Inc. is ISO 17025 accredited by A2LA for the test methods listed on the referenced certificates.



August 6, 2019

Jim Stock Tian's International, Inc. Page 2 of 3 PN 149079

SUBJECT:

Permeation testing per ASTM D 6978 on sample submitted by the above company.

RECEIVED:

Two (2) Gowns identified as; USP800 Barrier Gown.

TEST CHEMICALS:

Table 1. List of the Testing Drugs and their Sources

TESTING CHEMOTHERAPY DRUGS	DRUG SOURCE
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	Sigma Aldrich; Lot # 018M4057V; Expiration 04/2020
Thiotepa (THT), 10 mg/ml (10,000 ppm)	Sigma Aldrich; Lot# SLBZ3176, Expiration 05/2020

COLLECTION MEDIA:

Table 2. Collection Media for Test Chemicals

TEST DRUG AND CONCENTRATION	COLLECTION MEDIUM	
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	10% Ethanol Aqueous Solution	
Thiotepa (THT), 10 mg/ml (10,000 ppm)	Distilled Water	

TESTING CONDITIONS:

Standard Test Method Used:

Deviation from Standard Test Method:

Analytical Method:

Testing Temperature: Collection System:

Specimen Area Exposed:

Selected Data Points:

Number of Specimens Tested:

Location Sampled From:

ASTM D 6978

Used 1" Permeation Cell

UV/VIS Spectrometry

35.0°C ± 2.0

Closed Loop

5.067 cm2

25/test

3/test

Seam Area

Jim Stock Tian's International, Inc.

Page 3 of 3 PN 149079

DETECTION METHOD OF CHEMICAL PERMEATION:

UV/VIS ABSORPTION SPECTROMETRY:

Instrument:

Perkin Elmer UV/VIS Spectrometer Lambda 25

UV/VIS Absorption Spectrometry was used to measure the absorbance of test chemicals, which permeated through the specimens into the collection medium. The collection medium was circulated in a closed loop at 11 ml/minute of flow rate through the testing period. Data collection was performed according to the programmed schedule by means of UV Winlab software from the Perkin Elmer Corporation. The list of the characteristic wavelengths is shown below.

Table 3. Characteristic Wavelengths used in UV/VIS Absorption Spectrometry

TESTING DRUG	WAVELENGTH (nm)	
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	229	
Thiotepa (THT), 10 mg/ml (10,000 ppm)	199	

SAMPLE CHARACTERISTICS:

Table 4. Seam Thickness characteristics for the tested: USP800 Barrier Gown.

Tooting Drug	Thickness (mm)			A
Testing Drug	Sample 1	Sample 2	Sample 3	Average (mm)
Carmustine (BCNU)	0.485	0.539	0.276	0.433
Thiotepa (THT)	0.484	0.551	0.533	0.523
Weight/Unit Area (g/m2)	148.0			

RESULTS:

Table 5. Permeation Test Results on Seam Testing of: USP800 Barrier Gown.

TEST CHEMOTHERAPY DRUGS	MINIMUM BREAKTHROUGH DETECTION TIME (Specimen 1/2/3) (Minutes)	AVERAGE STEADY STATE PERM. RATE (Specimen 1/2/3) (μg/cm²/minute)	OTHER OBSERVATIONS
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	27.6 (27.6,27.6,28.4)	0.01 (0.01,0.01,0.01)	No significant changes
Thiotepa (THT), 10 mg/ml (10,000 ppm)	>240 min.	0	No significant changes

Prepared By

/ Jiffany Heller

Manager, Pharmaceutical Services

Approved By:

Ana C Barbur, M.S.

Vice President, Analytical & Chemical Services