# TRADIBATARD GF GRIS/BLANC One Coat Render (OCR), Weather-Resistant,

**Decorative Render** 





## **PRODUCT DESCRIPTION**

One coat, weather resistant render for use as a base coat or finishing coat internally and externally. For use as a base coat for finish coats such as MonoCal GM/GF.

#### **SUBSTRATES**

Masonry and walls conforming to BS 5628-3 and constructed from the following:

- Brickwork & Stonework
- Lightweight, & Dense Aggregate Blockwork
- Clay/Clinker Blocks PoroTherm
- Concrete
- Aircrete/Aerated light-weight Blocks
- Well bonded existing un-painted render
- VPI Specified Base Coats
- Below DPC applications as specified by VPI

#### **SUPPORTING PRODUCTS**

- Accrolor 2 Substrate Primer
- Monocal GM/GF & MonoPass GM/GF
- RenoPass Inter Painted Substrates
- VPI Mesh, VPI Latex & VPI FLASH
- Crepilane T-TM & Crepilor T-TM-GT-GF

# **TECHNICAL CHARACTERISTICS**

Cement, Lime, sand and mineral pigmented ready to use render.

PERFORMANCE @ +20°C

Type: OC2

Compressive Strength: CSII Capilary Absorption: W1 Vapour Permeability:  $\mu \le 35$ 

Reaction to Fire: A1 - Non-Combustible

#### **APPLICATION CONDITIONS**

- Temperature: +5°C +30°C.
- Do not apply in wet weather
- Do not apply if there is a risk of Frost or **Freezing Conditions**

#### **PRECAUTIONS FOR USE**

To protect your health and the environment, and for safe use of this product, follow the precautionary statements which are labelled on the packaging. You will find the safety instructions for this product in the Safety Data

#### **SUBSTRATE PREPARATION**

Please contact VPI UK Ltd for specific application procedures

- Substrate must be clean, dry, dust free: e.g: formwork oil, curing agent....
- Construction should conform to BS 5628 code of practice for use of masonry
- Remove excess render/plaster
- On Low and High suction substrates apply Accrolor 2
- VPI Mesh must be applied to all openings including windows, doors and all protrusions e.g air vents.
- On wet substrates apply a slurry/key coat of Tradibatard GF or approved base coat with VPI Latex – 1 part VPI latex to 3 parts water.

#### **PRODUCT PREPARATION**

Ensure the guidance for mixing including water settings/proportions are followed.

- Mix 6.3 6.8 Litres of clean water per 25kg
- Product should be continuously mixed for a minimum of 5 minutes
- For machine application 10-12 water pressure

VPI UK Ltd can provide project specific application procedures and specifications that meet the guidance set out by the NHBC in the guidance for render 6.11 2017. The VPI range of cement/lime renders are supplied ready to use only the addition of clean water is required for mixing and application via hand or spray application.

# **PRODUCT OPEN TIMES AT 20°C**

- Product useable life: 1 Hour
- Time between coats: 4 Hours to 3 Days
- Setting times 3 to 8 Hours

#### **APPLICATION:**

Please refer to the substrate preparation requirements for High Exposure or Coastal locations please refer to VPI guidance for enhanced weather protection in increase exposure zones.

Tradibatard GF can be applied by hand or bay machine application.

## WEATHERPROOFING COAT ONTO SUITABLE **MASONRY SUBSTRATES:**

**SCRAPED FINISH** 

Apply in one coat for spray application or two coats for hand application a compact, lined and level 18mm coat of Tradibatard GF to the substrate, level and line using a straight edge, trowel, spatula to flatten the surface ensuring all air pockets are removed from the render. When sufficiently cured between 3-10 hours depending on weather conditions scrape the surface using a "I Bar" or "H Section" to ensure the render surface is flat/free of undulations and finish using a scraping tool to leave a 15mm finished thickness of render. The finish should be an even texture, colour and finish leaving an aesthetically pleasing finish.

Adjoining elevations must be finished at the same time using the same application method and the same curing time to ensure colour consistency.

Ensure all rendered areas should be checked to ensure there are no surface imperfections or defects such as "misses" which should be removed at the finishing stage.

Total finished render thickness should be a minimum of 15mm.

#### **SPRAY TEXTURE / ROUGHCAST FINISH**

Apply in one coat for spray application or two coats for hand application a compact, lined and level 10-12mm coat

of Tradibatard GF to the substrate, level and line using a straight edge, trowel, spatula to flatten the surface ensuring all air pockets are removed from the render.

Allow first coat of Tradibatard GF to dry for between 3 & 10 Hours and apply using a Tyrolien gun or render machine a textured finish 4-6mm thick depending on required texture building up textured finish in layers to ensure the first coat of Tradibatard GF is fully over coated. The more coats applied the heavier the texture that will be achieved

#### **CONSUMPTION**

Finished Thickness - 15mm - Scraped - 1 to 1.2m2 / 25kg bag Finished Thickness - 10mm - Scraped - 1.3 to 1.5m2 / 25g bag

## **PACKAGING & STORAGE**

25kgs bags - 48 bags per pallet 18-month shelf life - Stored in a cool dry, environment without contact with the ground at a consistent temperature.

#### **HEALTH & SAFETY**

Suitable protective clothing required when handling and using this product. The product contains materials which can cause an allergic reaction, irritation to eyes and harmful consumed.

Seek medical advice In case of contact with

Keep out of the reach of children and minors. Always read and follow the guidance set out in the Health and Safety data sheet for this product.

