

# Insulguard Ecobuilder™

Variable Name	N	Avg	S-pop	Min Value	Max Value	TGT	Units	Category
V4 - BASIS WEIGHT AVG	8	33.78	0.27	33.4	34.1	34	gsm	ASTM D3776-96
V5 - MD GRAB TENSILE AVG	8	25.3	2.5	23	31	20	lbf	ASTM D5034-95
V6 - MD GRAB ELONG AVG	8	73.86	4.53	65.3	80.3	52	%	ASTM D5034-95
V7 - CD GRAB TENSILE AVG	8	17.1	1	16	19	16	lbf	ASTM D5034-95
V8 - CD GRAB ELONG AVG	8	79.24	5.08	72.5	85.1	58	%	ASTM D5034-95
V9 - MD STRIP TENSILE AVG	8	1112.5	893.4	29	1824		g/cm	ASTM D5035
V10 - MD STRIP ELONG AVG	8	79.25	6.69	70.3	89.9		%	ASTM D5035
V11 - CD STRIP TENSILE AVG	8	915	360.5	32	1148		g/cm	ASTM D5035
V12 - CD STRIP ELONG AVG	8	80.59	6.28	69.8	89.5		%	ASTM D5035
V13 - MD TRAP TEAR AVG	8	7.86	0.53	7.2	8.6		lbf	ASTM D5733
V14 - CD TRAP TEAR AVG	8	11.3	0.62	10.5	12.2		lbf	ASTM D5733

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. This information reflects typical properties and should not be considered as specifications.