

BE-215 TDS

Property	Unit	Spec	Value	Test Method
Appearance	-	Semi-Matte		ASTM E284
Base Thickness	μm	175 ± 5		ASTM D645
Base Weight	g/m ²	245 ± 5		ASTM D646
Total Thickness	μm	215 ± 10		ASTM D645
Total Weight	g/m ²	290 ± 10		ASTM D646
Gloss	%	60°: 6.0 ± 2.0 85°: 15.0 ± 2.0	60° : 85° :	ASTM D2457
Whiteness (Lab)	-	L : 85.0 ≤ a : 0.0 ± 2.0 b : -1.0 ± 2.0	L : a : b :	ANSI T (D50/2°/Abs/No)
Optical Density (CMYK)	-	C : 1.81 ± 0.1 M : 1.69 ± 0.1 Y : 1.14 ± 0.1 K : 2.19 ± 0.1	C : M : Y : K :	MIMAKI JV33-160
Yellowness Index	-	33.0 ± 3		ASTM D1925
Pin Hole	-	size : 1.0mm ≥ 3 ea ≥		Square Meter
Dust	-	size : 1.0mm ≥ 3 ea ≥		Square Meter