

GLITTER

SPECIFICATIONS

Composition	र्ये Avarage Thickness	Carrier	Certifications		
PU	350 microns	Adhesive polyester	REACH n° 1907/2006/EU		
			OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 VEGANOK AZIENDAN. 1004		

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS ↓			TRANSFER SETTINGS ↓			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	120 gf	20 cm/sec	15 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	hot/cold

- → Mirror cut the design
- → Weed excess material
- > Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier hot/cold

PRODUCT HIGHLIGHTS

- → easy to cut and weed
- ightarrow perfect for trendy or fashion items
- → "WOW" effect
- NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ory cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Up to 40°C, inside-out	YES inside-out	NO	YES	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our Sales Office.



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



